

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
25 October 2001 (25.10.2001)

PCT

(10) International Publication Number  
**WO 01/78688 A1**

(51) International Patent Classification<sup>7</sup>: **A61K 9/24**,  
31/4045, A61P 25/16

**MAGGI, Lauretta** [IT/IT]; Via Folperti, 3, I-27100 Pavia (IT). **CONTE, Ubaldo** [IT/IT]; Via Treviglio, 6, I-21052 Busto Arsizio (IT).

(21) International Application Number: PCT/GB01/01726

(22) International Filing Date: 12 April 2001 (12.04.2001)

(74) Agents: **BASSIL, Nicholas, Charles** et al.; Kilburn & Strode, 20 Red Lion Street, London WC1R 4PJ (GB).

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
MI2000A000852 14 April 2000 (14.04.2000) IT  
MI2000A001963 7 September 2000 (07.09.2000) IT

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(71) Applicant (*for all designated States except US*): **JAGOTEC AG** [CH/CH]; Eptingerstrasse 51, CH-4132 Muttenz (CH).

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant (*for LC only*): **BASSIL, Nicholas, Charles** [GB/GB]; Kilburn & Strode, 20 Red Lion Street, London WC1R 4PJ (GB).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): **VERGNAULT, Guy** [FR/FR]; 9, rue du Bois Vert, F-68300 Saint Louis (FR). **GRENIER, Pascal** [FR/FR]; Résidence la Clef des Champs, 5, rue des Vignes, F-68510 Kappelen (FR).

Published:

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: HYDROPHILIC/LIPOPILIC POLYMERIC MATRIX DOSAGE FORMULATION

(57) Abstract: An oral dosage form comprising a pharmaceutical tablet of one or more layers, one of which carries a biologically active substance; the formulation of said tablet includes different percentages of hydrophilic and lipophilic polymeric materials, and adjuvant substances. The tablets of the present invention show a release rate which is independent from the amounts of active substance present in the tablet.

WO 01/78688 A1

## HYDROPHILIC/LIOPHILIC POLYMERIC MATRIX DOSAGE FORMULATION

The present invention relates to a dosage formulation or tablet comprising a mixed matrix of hydrophilic and lipophilic components able to control the release rate of one or more therapeutically active agents from the formulation/tablet.

Recent years have seen considerable efforts made in the pharmaceutical technology field of research aimed at preparing innovative pharmaceutical forms, meant for the administration of active substances, both in human treatment and the veterinary field. One of the fundamental aspects of the innovative qualities of pharmaceutical dosage forms and/or prepared formulation systems is the potential targeting the release of the drug (or the active substance) to a specific site of action and/or of releasing such active substances with an *a priori* programmable velocity which can be assessed by way of suitable "*in vitro*" tests.

Other sectors are also interested in these technical fields, not just the human health sector, namely veterinary and agricultural sectors, especially with regard to the controlled release of fertilisers, weedkillers, insecticides and/or specific protection agents for certain cultures.

There are many examples in the pharmaceutical sector which describe the preparation of pharmaceutical forms capable of releasing the active principle (active substance) with zero kinetics. As is well known to experts in the field, this means that the active principle carried is given up by the pharmaceutical form at a constant velocity through time and for a programmable time period. In particular, the release of a drug can be expressed by the following empirical relation:

$$M_t/M_0 = Kt^n$$

the fraction of drug released ( $M_t/M_0$ ) is proportional to a constant K which depends on the diffusion coefficient in the matrix, whereas the constant n depends on the swelling characteristics and the relaxation velocity of the polymeric chains on the swelling

front. There are many examples of such pharmaceutical forms, for example, is quoted in the volume of S. Dimitriu "Polysaccharides in medical applications" M. Dekker, New York 1996.

5 There are many examples and pharmaceutical applications that concern dosage forms utilisable for different administration forms namely oral, transdermal, vaginal and ocular. Certainly, given the extreme importance and the widespread use of oral drug administration, the more numerous and differentiated embodiments are those aimed at releasing the active principle in the gastrointestinal tract, for example, the OROS  
10 system described in US 4,160,020.

Further progress in this field is also provided by the pharmaceutical oral dosage forms described in US 4,839,177 and US 5,422,123 (equivalent to EP-A-0226884 and EP-A-0432607 respectively) which describes the preparation of pharmaceutical forms for  
15 oral use capable of guaranteeing the liberation of an active principle at a constant release velocity, i.e. according to zero kinetics ( $n=0$  in the above formula). In particular, these documents describe the preparation of a therapeutic system consisting, in its simplest form, a hydrophilic matrix containing a drug and suitable excipients, capable of allowing the release of the active principle at varied rates (i.e. at  
20 controlled rates of release).

Constituent components important in causing the slowed release of the active principle are the hydrophilic polymers, which may be gellable, and are capable of swelling upon contact with water and/or aqueous fluids, forming a gelled layer from which the active  
25 principle spreads according to Fickian type kinetics.

The therapeutic system described above in US 4,839,177 and US 5,422,123 is characterised in that one part of said matrix is covered by an impermeable barrier (obtained by the application of a polymeric film which is insoluble in water and  
30 aqueous medium as in US 4,839,177 or in that a layer of material and/or a polymeric material mix is applied by compression (possibly granulates obtained in accordance with known techniques) thus giving impermeability and/or, in any case, impeding the

release of the drug carried in the matrix form the protected surface for a predeterminable time period (as in US 5,422,123). The result is that the release of the active principle carried in the hydrophilic matrix only occurs from the free surface of the layer containing the active substance in direct contact with the dissolution medium.

5 Such a system is characterised in that the active principle, carried in said pharmaceutical forms, is given up at a velocity which generally proves constant over time (zero release kinetics) as is highlighted in the claims of the cited patent.

10 Other tablet formulations have provided for the liberation of one or more drugs at different release rates (WO 94/06416) by appropriate formulation of the layers in the multi-layer tablet. Alternative phased drug release systems have described the use of an impermeable membrane to control the time of drug release (US 5,487,901), a complete coat of a biodegradable polymeric material (US 6,027,748), or a more substantial layer of controlled permeability materials (EP-A-0788790). Still further  
15 multi-layer tablets have been described in which the tablet shows a high volume increase on contact with the contents of the stomach so as to provide for prolonged gastric residence times (EP-A-0795324).

20 However, in many treatment protocols, the patient must take drugs for extended time periods, for chronic disease treatment and must follow, at times, complex posological patterns, taking two or more pharmaceutical forms over 24 hours. Such complex and distinct therapeutic models are poorly supported and infrequently followed by non-hospitalised patients; in fact, the withdrawal of the correct observance of the posological models is very frequent and well known in the case of outpatients, and  
25 such a withdrawal is directly proportional to the complexity and number of administrations required or recommended during the day. For example, in the treatment of chronic diseases, for example hypertension the posology of the drugs must be adjusted in relation to the seriousness of the pathology and hence personalised to the specific therapeutic needs of the individual concerned.

30

Of importance to many pathological models, is the request by the medical profession to make available pharmaceutical forms with a very differentiated active principle

content (so as to favour the personalisation of the posology), which however are able to release the drug with similar or equivalent velocity and release kinetics, independent from the amount of active substance carried.

5 Therefore the availability of pharmaceutical forms which can release different dosages of the same drug at the same or similar velocity would provide the medical profession with a solution, to an important therapeutic problem, of major social relevance for the type of therapy at which it is directed. Such dosage forms would allow for the optimisation of drug use and biologically active substances in general.

10

It has now been discovered that utilising a particular formulation and pharmaceutical form consisting of a multi-layer tablet, preferably containing two or three layers, it is possible to obtain a similar or identical release velocity, even if said tablet carries very different amounts of the same active substance.

15

The originality of the new, prepared embodiment, in addition to the morphological and practical characteristics of the new therapeutic system are better illustrated in the following detailed description.

20 According to a first aspect of the invention there is provided a multi-layer tablet, in particular a multi-layer controlled-release tablet, comprising:

(a) one active layer containing: (i) an active substance, (ii) hydrophilic polymeric substances which swell and/or gel and/or erode upon contact with aqueous liquids, (iii) lipophilic substances, and (iv) adjuvant substances, wherein the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in said active layer is in the range of 10:1 to 0.5:1; and

30

(b) one or more barrier layers containing one or more of: hydrophilic polymeric substances which swell and/or gel and/or erode upon contact with aqueous liquids, lipophilic substances, and adjuvant substances.

Multi-layer tablets prepared in accordance with the present invention are able to provide substantially equivalent (or identical) release kinetics for the same active substance when formulated at different amounts in the active substance containing layer in the multi-layer tablet. The pharmaceutical tablets of the invention have the advantage of releasing the carried active substance in a programmed way, preferably also avoiding the phenomenon of dose dumping, and therefore being able to meet specific therapeutic needs with the gradual and controlled release of the active substance.

10

The multi-layer tablets of the present invention can be prepared as two-layer tablets, three-layer tablets or greater numbers of layers if required. At least one layer will contain the active substance to be released from the tablet and least one layer will be a barrier or support layer with respect to the active substance containing layer. Possible constructions of multi-layer tablets are shown in Figures 1 to 9. The tablets may have an overall substantially circular cross-section, or it may adopt a more oval cross-section or any other suitable geometric shape, for example rectilinear. The tablet may also be shaped as a caplet (capsule form tablet). As will be appreciated there are many potential arrangements of the layers in multi-layer tablets.

20

The layer containing the active substance can be referred to as the active layer, although, it should be noted that more than one active substance can be formulated in a tablet of the present invention. The layer that generally does not contain an active substance can be referred to as a barrier layer or a support layer.

25

A simple two-layer tablet is shown in Figure 1 where one lateral surface of the active substance containing layer (dotted) is covered by a barrier layer (hatched). A variation of this construction is shown in Figure 2 where two barrier layers cover both exposed lateral surfaces of the active substance containing layer. In Figure 3 a single barrier layer coats one lateral surface and the side of the active layer. The barrier layer is shown as being present in the form of an annular ring in Figure 4 surrounding the active core and Figure 5, an active core consisting of two active layers is shown

30

surrounded by an annular ring of a barrier layer.

In Figure 6 a three layer tablet is shown in which there is a first barrier layer (3) with an exposed upper lateral surface and sides, which is adjacent to a second active layer (2) with both lateral surfaces covered and the side of the layer exposed, which is in turn adjacent to a second active layer (1) where the bottom lateral surface is exposed and the side is exposed. The two active layers may contain different active substances or the same active substance in different amounts. Figure 7 shows an alternative arrangement of the Figure 6 embodiment, where the active substance layer (5) is wholly within the barrier layer (6) and the second active substance layer (4). In Figure 8, a similar three-layer tablet is shown in which the barrier layer (8) is interposed between the two active substance containing layers (9) and (7).

Another three layer tablet (caplet) construction is also shown in Figure 9 in which the tablet has two external barrier layers (10, 12) and an active substance layer (11) interposed between the barrier layers.

In some tablet configurations, the barrier layer may also contain an active substance such that it acts as a barrier layer with respect to a first active substance containing layer, but which itself is an active substance containing layer. Generally, in such embodiments, the active substance in the active layers is different in the separate layers, although arrangements in which the same active is present in the separate active layers in different amounts can also be envisaged..

The barrier layer(s) are meant to limit the release surface of the active layer, so as to allow that said carried active substance is released by the sole uncovered surface upon contact with the dissolution medium and/or the biological fluids according to kinetics that, *in vitro*, can be programmed according to precise methods, as will be highlighted in the given examples of the present invention.

Any pharmaceutically active substance suitable for oral administration in the form of a tablet can be formulated in a tablet of the present invention. An active substance is

therefore a pharmaceutical (drug) with a therapeutic use, such substances also include those for administration for non-therapeutic uses, such as diagnosis of for dietary purposes.

- 5 Preferably the active substance may be one aimed at the treatment of chronic diseases, for example, drugs acting on the cardiovascular system, anti-arrhythmics, cardiac stimulants, vasodilators, calcium antagonists, anti-hypertensives, for example anti-adrenergic substances of central and peripheral action or substances acting on the arteriolar musculature, analgesic substances, substances acting on the renin-  
10 angiotensin system, anti-hypertensives and diuretics in association, anti-Parkinson's Disease agents, diuretics and drugs for the treatment of Alzheimer's disease, anti-histamines and/or anti-asthmatics.

- Examples of active substances which may be used in such pharmaceutical forms are:  
15 propranolol, atenolol, pindolol, ropinirole, prazosin, ramipril, spirapril; spironolactone, metipranolol, molsidomine, moxonidina, nadolol, nadoxolol, levodopa, metoprolol, timolol. In a particular preferred embodiment, the active substance (i) comprises or is ropinirole, inclusive of pharmaceutically acceptable salts thereof.

- 20 Ropinirole, its chemical structure, processes for its preparation and therapeutic uses thereof, are more fully described in EP-A-0113964 (see Example 2), EP-A-0299602, EP-A-0300614, WO 91/16306, WO 92/00735 and WO 93/23035, and the contents of which are hereby incorporated by reference. "Ropinirole" as mentioned herein is defined as including pharmaceutically acceptable salts thereof. Most preferably, the  
25 ropinirole used in the tablet is in the form of the hydrochloride salt. Ropinirole is presently marketed as the HCl salt in an immediate-release tablet for the treatment of Parkinson's Disease (see also EP-A-0299602). Ropinirole can be synthesised by the advantageous method described in WO 91/16306.

- 30 In embodiments of the invention in which the active substance comprises or is ropinirole, the amount of ropinirole present, inclusive of pharmaceutically acceptable salts thereof, may be up to 12.0mg, preferably from 0.75mg to 12.0mg, measured as



the amount of ropinirole base present, that is excluding any amount of acid (for example, hydrochloric acid, HCl) added to form any ropinirole salts. The amount of ropinirole present, inclusive of pharmaceutically acceptable salts thereof, may be up to 12.0mg, preferably from 0.75mg to 12.0mg, measured as the amount of ropinirole base present, per 150 mg of active layer present. See Examples 13 to 18 hereinafter.

Analgesic substances include, but are not limited to, steroidal anti-inflammatory drugs, opioid analgesics, and non-steroidal anti-inflammatory drugs (NSAIDs). The analgesic substance may be a non-steroidal anti-inflammatory drug (NSAID), such as acetylsalicylic acid, salicylic acid, indomethacin, ibuprofen, naproxen, naproxen sodium, flubiprofen, indoprofen, ketoprofen, piroxicam, diclofenac, diclofenac sodium, etodolac, ketorolac, or the pharmaceutically acceptable salts and/or derivatives or mixtures thereof.

Other suitable analgesic substances include, but are not limited to opioid analgesics such as alfentanil, allylprodine, alphaprodine, anileridine, benzylmorphine, bezitramide, buprenorphine, butorphanol, clonitazene, codeine, cyclazocine, desomorphine, dextromoramide, dezocine, diampromide, dihydrocodeine, dihydromorphine, dimenoxadol, dimepheptanol, dimethylthiambutene, dioxaphetyl butyrate, dipipanone, eptazocine, ethoheptazine, ethylmethylthiambutene, ethylmorphine, etonitazene, fentanyl, heroin, hydrocodone, hydromorphone, hydroxypethidine, isomethadone, ketobemidone, levallorphan, levorphanol, levophenacylmorphan, lofentanil, meperidine, meptazinol, metazocine, methadone, metopon, morphine, myrophine, nalbuphine, narceine, nicomorphine, norlevorphanol, normethadone, nalorphine, normorphine, norpipanone, opium, oxycodone, oxymorphone, papaveretum, pentazocine, phenadoxone, phenomorphan, phenazocine, phenoperidine, piminodine, piritramide, proheptazine, promedol, properidine, propiram, propoxyphene, sufentanil, tramadol, tilidine and pharmaceutically acceptable salts and/or derivatives or mixtures thereof.

Anti-hypertensive drugs may include, diltiazem, trapidil, urapidil, benziadarone, dipiridamole (dipyridamole), lidoflazine, naphthydrofuryl oxalate, perhexeline

maleate, oxyfedrine hydrochloride. Anti-histamines and/or anti-asthmatics may include ephedrine, terfenadine, theophylline or chlorpheniramine.

5 In any case the matrices can be prepared, carrying any type of active principle for which pharmaceutical forms may be necessary capable of releasing also very different amounts of active substance with the same release kinetics.

10 In the tablets of the present patent application, the active substance to be carried may have a very wide solubility interval in water, e.g. between 0.01 mg/L up to 3000 g/L, preferably between 10 mg/L up to 1000 g/L (e.g. ropinirole has 133 g/L solubility), or between 0.01mg/L up to 100 g/L.

15 The active substance is preferably contained in a percentage between 0.05% to 50% by weight of the active layer; more preferred ranges of the active substances are 0.05% to 40%, 0.05% to 30%, 0.05% to 10%, 0.05% to 20%.

20 Natural or synthetic hydrophilic polymeric substances, can be used in the preparation of said active layer which are biocompatible and/or biodegradable materials and pharmaceutically acceptable, e.g. polyvinylpyrrolidone in particular non-cross-linked polyvinylpyrrolidone (e.g. of molecular weight 30,000-400,000), hydroxypropylcellulose with a molecular weight of from 100,000 to 4,000,000, sodium carboxymethylcellulose (e.g. non-cross-linked, e.g. typical molecular weight 90,000-700,000), carboxymethylstarch, potassium methacrylate-divinylbenzene copolymer, hydroxypropylmethylcellulose with a molecular weight between 2,000 and 25 4,000,000, polyethyleneglycols of different molecular weight preferably between 200 and 15,000 (more preferably 1000-15000) and polyoxyethylenes of molecular weight up to 20,000,000 (more preferably 400,000-7,000,000), carboxyvinylpolymers, poloxamers (polyoxyethylene-polyoxypropylene copolymer), polyvinylalcohols, glucanes (glucans), carrageenans, scleroglucanes (scleroglucans), mannans, 30 galactomannans, gellans, xanthans, alginic acid and derivatives (e.g. sodium or calcium alginate, propylene glycol alginate), polyaminoacids (e.g. gelatin), methyl vinyl ether / maleic anhydride copolymer, carboxymethylcellulose and derivatives

(e.g. calcium carboxymethylcellulose), ethylcellulose, methylcellulose, starch and starch derivatives, alpha, beta or gamma cyclodextrin, and dextrin derivatives (e.g. dextrin) in general. The hydrophilic polymeric substance is therefore one which can be described as a controlled release polymer or a polymeric substance which is capable of achieving controlled release (CR).

More preferably for achieving advantageous controlled release of the active substance the hydrophilic polymeric substances in the active layer comprise one or more of the following: hydroxypropylcellulose with a molecular weight of from 100,000 to 4,000,000, hydroxypropylmethylcellulose (HPMC) with a molecular weight between 2,000 and 4,000,000 (more preferably between 10,000 and 1,500,000 molecular weight, still more preferably between 20,000 and 500,000 molecular weight, most preferably about 250,000 molecular weight), ethylcellulose or methylcellulose. The most preferred controlled release polymer is HPMC.

Hydrophilic polymeric substances such as sodium carboxymethylcellulose and/or calcium carboxymethylcellulose that act as viscosity-increasing agents/polymers or "cage-forming" components are also preferred components e.g. of the active layer. The provision of these viscosity-increasing polymers in the active layer is preferred because these help to reduce the "dose-dumping" effects occasionally seen with soluble active substances (e.g. ropinirole) whereby a significant minority of the active substance can be released from the active layer in the first (say) hour after oral administration. Thus, it is preferred for this purpose that the hydrophilic polymeric substances in the active layer comprise sodium carboxymethylcellulose, carboxymethylcellulose or a derivative (e.g. calcium carboxymethylcellulose), hydroxypropylcellulose with a molecular weight of from 100,000 to 4,000,000, a carboxyvinylpolymer, a carrageenan, a xanthan, alginic acid or a derivative (e.g. sodium or calcium alginate, propylene glycol alginate), ethylcellulose, methylcellulose, dextrin and/or maltodextrin. Most preferred for this purpose is sodium carboxymethylcellulose (NaCMC) (e.g. non-cross-linked, e.g. typical molecular weight 90,000-700,000). The present invention also comprehends the use of other equivalent polymers able to act as viscosity-increasing agents and/or "cage-

forming" components.

It is more preferred that the hydrophilic polymeric substances in the active layer comprise both the above-mentioned preferred controlled release polymers and the above-defined viscosity-increasing polymers. Thus it is preferred that the hydrophilic polymeric substances in the active layer comprise:

(a) one or more of the following: hydroxypropylcellulose with a molecular weight of from 100,000 to 4,000,000, hydroxypropylmethylcellulose (HPMC) with a molecular weight between 2,000 and 4,000,000, ethylcellulose or methylcellulose; and

(b) sodium carboxymethylcellulose, carboxymethylcellulose or derivatives (e.g. calcium carboxymethylcellulose), hydroxypropylcellulose with a molecular weight of from 100,000 to 4,000,000, a carboxyvinylpolymer, a carrageenan, a xanthan, alginic acid or a derivative (e.g. sodium or calcium alginate, propylene glycol alginate), ethylcellulose, methylcellulose, dextrin and/or maltodextrin.

Thus, while the controlled release polymer (a) such as HPMC is still swelling and/or gelling gradually in the first hour-or-so after oral administration of the tablet, when it may be less effective in controlling release of soluble active substances such as ropinirole from the active layer, the viscosity-increasing polymer (b) such as sodium carboxymethylcellulose (NaCMC) reduces the release of the active substance from the active layer. Without being bound by theory, ionic viscosity-enhancers like NaCMC might also to interact with the hydroxypropyl groups of, for example, HPMC to boost synergistically the hydration and swelling rate of HPMC leading to greater gel strength.

Thus, the most preferred combination is that the hydrophilic polymeric substances in the active layer include (or are) HPMC and sodium carboxymethylcellulose, especially when the active substance has a high (e.g. from 10 mg/L to 1000 g/L) solubility in water, such as ropinirole.

Preferably, the hydrophilic polymeric substances have an HLB value of at least 10 (see A. Gennaro and J. Remington, Remington's Pharmaceutical Sciences, 18<sup>th</sup> edition,

Mack Publishing Company, Easton, Pa., 304 (1990) and W.C. Griffin, *J. Soc. Cosmetic Chemists*, vol. 1, page 311, 1949 for HLB values and measurement thereof). Said hydrophilic polymeric substances make up between 1% and 75% of the weight of the active layer, but preferably are present in a percentage between 5% and 65% and/or between 30 and 75%, more preferably 43-75% or 43-67% or 43-65%. Any HPMC present in the active layer is preferably present in about 40-63 % by weight of the active layer. The viscosity-increasing polymers mentioned above, such as sodium carboxymethylcellulose, if present are preferably present in up to 20% by weight of the active layer, more preferably (especially for NaCMC) 3-20%, 5-20%, 7-15%, or about 10% by weight of the active layer.

For all the polymers cited different types are commercially available characterised by different chemical, physical, solubility and gelification properties. In particular, as regards, hydroxypropylmethylcellulose various types with a different molecular weight (between 1,000 and 4,000,000, preferably from 2,000 to 4,000,000, even more preferably between 10,000 and 1,500,000 molecular weight, still more preferably between 20,000 and 500,000 molecular weight, most preferably about 250,000 molecular weight) can be used and with different degrees of substitution. Said types of hydroxypropylmethylcellulose have differentiated characteristics being mainly erodible or able to be gelled, depending on the viscosity and the degrees of substitution (D.S.) present in the polymeric chain. Gellable HPMCs (e.g. Methocel K grades) are preferable to erodible HPMCs (e.g. Methocel E grades). The polyethyleneglycols and polyoxyethylenes show identical behaviour: in fact, different hydrophilic and gelification properties correspond to different molecular weights.

The molecular weight of polymers and the 2% viscosity of polymers can be directly correlated ("METHOCEL<sup>TM</sup> in Aqueous Systems for Tablet Coating", page 12, published by The Dow Chemical Company - [www.dow.com](http://www.dow.com) - METHOCEL<sup>TM</sup> is a trademark of The Dow Chemical Company) where viscosity of a polymer is defined as viscosity of a 2% aqueous solution at 20°C measured as mPa. seconds. Viscosity is measured in Pascal seconds (SI units) or in poise (c.g.s. units), where 1 centipoise =  $10^{-3}$  Pa.sec. So for example, METHOCEL<sup>TM</sup> K100M has an approximate molecular

weight of 246,000 and a corresponding 2% viscosity of 100,000 mPa.sec (based on an average viscosity of 80,000 to 120,000 mPa.sec.); METHOCEL™ K4M has an approximate molecular weight of 86,000 and a corresponding 2% viscosity of 4,000 mPa.sec; and METHOCEL™ K100LV has an approximate molecular weight of 27,000 and a corresponding 2% viscosity of 100 mPa.sec. For this reason, the preferred molecular weight ranges of the polymeric substances, for example the hydroxypropylmethylcellulose polymers can also be defined in terms of viscosity.

One preferred viscosity range for the hydroxypropylmethylcellulose polymers as defined above may be in the range of from 50 to 150,000 mPa.sec, suitably 80,000 to 120,000 mPa.sec (e.g. K100M, as in the active and barrier layers of Examples 13-21). This applies both to the active layer (discussed above) or the barrier / support layer(s) (discussed below).

In an alternative embodiment, in order to obtain a faster release rate, the viscosity range for the hydroxypropylmethylcellulose polymers in the active and/or barrier layer(s) may be in the range of from 50 to 25,000 mPa.sec (including Methocels K4M, K15M, K100LV). In this embodiment, preferably some or all of the HPMC polymers have a viscosity in the range of from 1000 to 25,000 mPa.sec (including Methocels K4M & K15M but not K100LV or K100M). More preferably, HPMC polymers having a viscosity in the range of from 1000 to 25,000 mPa.sec are present in the active or barrier layer in a percentage of from 5 to 50% by weight of the active or barrier layer. In particular, Examples 22 and 23 hereinafter have 10% and 40 weight % respectively of such HPMC (K4M) in their barrier layers which gives a slightly faster release profile *in vitro* than the ca. 45 wt% K100M HPMC present in the barrier layers of Examples 13-18 and 19-21, as *inter alia* the active substance e.g. ropinirole migrates faster through the barrier layers. Preferably, the proportion of low-viscosity HPMCs having from 50 to <1000 mPa.sec viscosity (including Methocel K100LV) contained in the active or barrier layers is less than 30% by weight of that layer – e.g. Example 22 has 20 wt % of such HPMC (K100LV) as well as 10 wt % K4M HPMC in the barrier layer. Up to 30% low-viscosity HPMC in active or barrier layer can increase water uptake and aid gelling, increasing the matrix viscosity and decreasing

the release rate, but greater amounts are not preferred.

In an alternative embodiment of the invention, there is provided a tablet as previously defined, in which the active layer contains polymeric material with slow swelling  
5 and/or gellification and/or erosion and/or solubility properties.

A fundamental characteristic of the tablets of the present invention is that, for the formulation both of the layer containing the active substance and the barrier layers, lipophilic substances are utilised, for example natural fats (coconut, soya, cocoa) as  
10 such or totally or partially hydrogenated, beeswax, polyethoxylated beeswax, mono-, bi- and tri-substituted glycerides, glyceryl palmitostearate, glyceryl behenate (glyceryl tribehenate  $C_{69}H_{134}CO_6$ , e.g. Compritol 888, where behenic acid = docosanoic acid =  $C_{21}H_{43}COOH$ ), diethyleneglycol palmitostearate, polyethyleneglycol stearate, polyethyleneglycol palmitostearate, polyoxyethylene-glycol palmitostearate, glyceryl  
15 monopalmitostearate, cetyl palmitate, mono- or di- glyceryl behenate (glyceryl mono-behenate or glyceryl di-behenate), fatty alcohols associated with polyethoxylate fatty alcohols, cetyl alcohol, stearic acid, saturated or unsaturated fatty acids and their hydrogenated derivatives, hydrogenated castor oil and lipophilic substances in general. In certain preferred embodiments of the invention, the lipophilic substances are  
20 selected from hydrogenated castor oil and glyceryl behenate.

Preferably, the lipophilic substances have an HLB value of less than 10, more preferably, less than 5.

25 Preferably, the lipophilic substances make up between 1% and 70% of the active layer weight, but preferably are present in a percentage between 5% and 55%, more preferably 5-35%.

The weight ratio between the content of hydrophilic polymeric substances and  
30 lipophilic substances, in the layer containing the active substance, is between 10:1 and 0.5:1 (i.e. in the range of 10:1 to 0.5:1), suitably between 10:1 and 1:1 (i.e. in the range of 10:1 to 1:1), but preferably between 7:1 and 1:1 (i.e. in the range of 7:1 to 1:1).

Besides the previously cited hydrophilic polymers and the lipophilic substances, lipophilic and/or substances of amphiphilic nature may be used in the formulation, in which the hydrophilic portion can be represented by glycerol molecules or other  
5 polyalcohols or polyethyleneglycol molecules (PEG) of molecular weight between 100 and 10,000, whereas the lipophilic part is represented by unsaturated and/or saturated fatty acids, in hydrogenated vegetable oil form. The association of the hydrophilic portion with the lipidic chain is obtained by esterification reactions or partial alcoholysis of hydrogenated vegetable oils by PEG molecules or glycerol or  
10 other polyol. In this way compounds characterised by a different degree of hydrophilicity are obtained that can be assessed by measuring the Hydrophilic-Lipophilic Balance (HLB). Triglycerides are available with an HLB value between 1 and 2, diglycerides with HLB between 2 and 3, monoglycerides with HLB between 3 and 4, PEG diesters with HLB between 6 and 15, PEG monoesters with HLB between  
15 10 and 17. In practice, increasing the HLB values increases the hydrophilic tendency and, obviously, decreases the lipophilic tendency. Tablets according to the present invention may therefore also contain polymeric substances of a lipophilic nature.

Finally, adjuvants normally used in the pharmaceutical technique may be employed,  
20 for example, diluents, binders, lubricants, glidants and non-stick types, for example, starch, mannitol, lactose, sorbitol, xylitol, talc, stearic acid, sodium benzoate, magnesium stearate, colloidal silica, maltodextrin, and other excipients known to the expert in the field.

25 In order to promote the penetration of water and/or aqueous fluids in the layer or nucleus, hydrophilic diluents, for example, mannitol, lactose, starches of different origins, sorbitol, xylitol are introduced, or substances with wetting properties and/or those generally encouraging the penetration of water in the solid are preferably carried in the formulation.

30 Moreover, diluents, binders, lubricants, buffers, non-stick substances, glidants and plasticising substances can be employed as well as others capable of giving said layer



the desired characteristic as will be better illustrated in the examples quoted later on.

Said adjuvants are preferably contained in a percentage between 5% to 50%; preferably from 10% to 40% or 20 to 50 % or 20% to 35% of the weight of said active layer. The weight ratio of the active substance (i) to that of the adjuvant component (iv) in the active layer can be in the range of from 0.001:1 and 4:1, suitably of from 0.003:1 to 3:1.

The polymeric substances employed for the preparation of the barrier layer in association with other adjuvants, are able to provide a barrier (applied by compression) which proves impermeable to the carried active substance in the underlying layer for a time period that strictly depends on its composition, which can vary from 1 hour to approx. 20-24 hours or more. In such case, the release of the active substance in the stated periods (e.g. during the first hour after oral administration / immersion in aqueous fluids) occurs only from the surface of the tablet not covered by the barrier. "Impermeability" is to be construed accordingly. Preferably, during the first hour after oral administration or immersion in aqueous liquids (e.g. water), release of the active substance occurs substantially only from the surface of the tablet not covered by the barrier.

To test the impermeability of the barrier layer to the release of the active substance, various suitable tests can be conceived by persons skilled in the art of pharmaceutical tablet formulation. However, one such test may be based on selective coating of the free surfaces of the active layer with a suitable substance, such as an enteric coat (for example, "Eudragit"), or a waxy material (for example, beeswax) such that normal release of active does not occur through these surfaces. An *in vitro* dissolution test can then be performed in which the dissolution fluid can be sampled at appropriate time points. In this way, the point in time can be determined at which the active substance is released through the barrier layer through the interaction of the component substances of the barrier layer with the aqueous environment (that is to say the point in time at which the polymers of the barrier layer permit release). Alternatively, the free surfaces of the barrier layer(s) can be selectively coated as above and a dissolution test

performed. The release profile obtained would correspond to that of an uncoated tablet up to the point in time at which the active substance was able to permeate the barrier layer and be released from the uncoated tablet.

5 As noted above, the barrier layer may be superposed over one or more free surfaces of the active layer in the tablet. Generally, the barrier layer will form a layer to cover one or more lateral surfaces of the active layer. In a preferred embodiment of the present invention, tablets are provided in which one or more barrier layers are used to cover one or both surfaces or bases of the active layer. Such arrangements therefore provide  
10 for a bi-layer or a tri-layer tablet.

The natural synthetic hydrophilic polymeric materials, usable in the formulation of the barrier layer, can be chosen from among those listed for the preparation of the active layer. Said polymeric substances can be present in a percentage of 5 to 90%, with  
15 respect to the total weight of said layer but, preferably, between 25% and 85%.

Said polymeric substances, utilised individually or mixed together and mixed with the lipophilic substances, are able to bring about the impermeability in the release of the carried active principle in the underlying layer for a time interval that can vary from 1  
20 hours to approx. 20-24 hours or more, depending on the composition.

For the preparation of the barrier layer such lipophilic substances can be chosen from those listed for preparation of the active layer. Said lipophilic substances can be present in a percentage between 5% and 70% with respect to the total weight of said  
25 layer but, preferably, between 5% and 55%.

The weight ratio of hydrophobic swelling and/or gelling and/or erodible polymeric substances to lipophilic substances contained in the barrier layer can be in the range of 1:1 and 7.5:1, suitably of from 1.5:1 to 4:1, and preferably from 2:1 to 3.5:1.  
30

Said barrier layer(s), applied by compression, can have a thickness between 0.1 and 4.5 mm. The matrix preparation can be carried out by the compression of powder or

granular mixtures, for example by blending followed by dry compression or wet granulation followed by compression, and preferably working between 1000 and 5000 Kg/cm<sup>2</sup>.

- 5 In general, tabletting can be through direct compression, i.e. a mixture of dry powders being compressed, but this can sometimes cause quality issues such as segregation, poor flow etc. These issues can be improved by the use of granulation techniques on all or part of the constituent mix.
- 10 Granulation is a process in which powder particles are agglomerated together to form granules. This can be carried out to:
1. improve the flow properties of a powder mixture,
  2. prevent segregation of the constituent powders (improve homogeneity),
  3. improve compression characteristics,
  - 15 4. achieve densification of powder mixes, and/or
  5. achieve alteration of particle size/shape/hydrophilic properties

The tablet of the invention may be prepared by dry granulation. Dry Granulation is granulation by compression of powders by either slugging or roller compaction. It is  
20 essentially a densification process.

Slugging is where a crude compact (slug) is produced to a set weight/thickness for a given diameter of slug. These slugs are then reduced by either grating or commuting mill to produce granules of the required particle size/range.

25 Roller compaction or Chilsonating is where a powder mix is forced via an auger between 2 rollers (which can be smooth or grooved). Compaction of this material is controlled by the feed rate to the rollers and the hydraulic force of the rollers being pushed together. The resulting compact (called a ribbon or strip) is then reduced by  
30 either grating or commuting mill to produce granules of the required particle size/range.

Where dry granulation is used, the adjuvants often differ slightly compared to wet granulation. For example, instead of lactose monohydrate (often used in wet granulation), one preferably uses spray-dried lactose preferably containing amorphous lactose (e.g. Fast-Flo lactose, Seppic, Paris, France).

5

However, the tablet of the invention is preferably prepared by wet granulation. Wet Granulation is the most widely used granulation technique, and involves powder densification and/or agglomeration by the incorporation of a granulation fluid/medium to the powder mix. Wet granulation can be aqueous-based or solvent-based, e.g. based on organic solvents. Shear is dependent on the speed of the granulator paddle/blade through the powder. Various mixer designs are available, for example:

10

Wet High Shear, (rotating high shear forces (Felder))

Wet Low Shear, (rotating low shear forces (Planetary mixer))

Wet Low Shear Tumble, ( spraying in to tumble mixer with/without intensifier bar)

15

Extrusion, (Wet solids pushed through classified screen)

Rotary Granulators, (Spheronisation, Marumerisation – spinning disk or walls of a vessel)

Spray granulation in a fluidised Bed, or

20

Spray dry granulation.

For the formulation of said layer-barrier, which can be applied by compression, possible adjuvants, in particular diluents, include those traditionally used in the preparation of solid forms. For example magnesium stearate, stearic acid, sodium stearate, talc, sodium benzoate, boric acid, polyethylene glycols and/or colloidal silica can be employed.

25

In addition diluent, lubricating, non-stick and glidant substances and other substances may be used capable of giving said layer the desired characteristic, as will be better illustrated in the examples quoted later on. Other possible components include substances able to impart a colour to the eventual tablet layer prepared and formulated in the multi-layer tablet, for example iron oxide (yellow ferric oxide).

30

In addition a covering could be applied to said finished tablets by a coating process and/or any other process well known to experts in the field. An example of a coating is "OPADRY OY-S-28876 WHITE". OPADRY OY-S-28876 WHITE is 63% HPMC 2910 6cP, 7% PEG 400, 30% TiO<sub>2</sub>. Red/pink (0.01-0.25%) and/or yellow (0.1 to 1.5%) colourings can also be added (iron oxides), the HPMC varying between 61-66%. An alternative blue coating uses 31-32% each of HPMC 2910 3cP and HPMC 2910 5cP, 8% PEG400, 23-24% TiO<sub>2</sub>, 1% polysorbate, and indigotine as blue dye at 4-5%.

A colourant layer or a film of gastroresistant and enterosoluble polymeric material may also be applied to said finished tablets, so as to allow the activation of the system only after the tablet has reached the duodeno-intestinal tract. Pharmaceutical systems of the latter type can be utilised for the accomplishment of tablets specifically designed to release the active principle in the latter part of the intestinal tract i.e. at colon level. In order to attain gastroresistance, polymeric materials such as cellulose acetophthalate, cellulose acetopropionate, cellulose trimellitate, polymers and acrylic and methacrylic copolymers can be used of different molecular weights and with solubility which depends on different pH values. Said materials can be applied to the finished pharmaceutical form (active layer and the barrier layer(s)) by the classical coating process, utilising solutions in organic solvents or aqueous dispersions and spraying or fluidised bed nebulisation. Said gastro-resistant and enterosoluble materials can likewise be utilised in association with retarder polymers.

One innovative embodiment is characterised in that it is possible to achieve the claimed therapeutic system by utilising the production technologies currently in use, i.e. the system may be immediately set up at industrial level.

One preferred embodiment of a tablet of the present invention comprises a tablet as previously described in which the active layer consists of components (i) to (iv) wherein the active agent is present in a weight percentage of 0.05% to 20% by weight of the active layer, the adjuvant substances are present in a weight percentage of 5% to

50% by weight of the active layer, and the weight ratio of the hydrophilic polymeric substances to the lipophilic substances is in the range of from 7:1 to 1:1.

Alternatively, the active layer consists essentially of components (i) to (iv) wherein the active agent is present in a weight percentage of 0.05% to 20% by weight of the active layer, the adjuvant substances are present in a weight percentage of 5% to 50% by weight of the active layer, and the weight ratio of the hydrophilic polymeric substances to the lipophilic substances is in the range of from 7:1 to 1:1.

In certain preferred embodiments, the hydrophilic polymeric substance may comprise hydroxypropylmethylcellulose of molecular weight 2,000 to 4,000,000, sodium carboxymethylcellulose or calcium carboxymethylcellulose.

In embodiments in which the active substance is ropinirole, the tablet may be characterised by comprising (i) ropinirole present in a weight percentage of 0.05% to 20% by weight of the active layer, (ii) the hydrophilic polymeric substance being hydroxypropylmethylcellulose, sodium carboxymethylcellulose or calcium carboxymethylcellulose. (iii) the lipophilic substance being hydrogenated castor oil or glyceryl behenate, and (iv) the adjuvant substances being present in a weight percentage of 5% to 50% by weight of the active layer, in which the weight ratio of the hydrophilic polymeric substances to the lipophilic substances being in the range of from 7:1 to 1:1.

The present invention also extends to methods of treatment comprising a tablet as herein described. According to a second aspect of the invention there is provided a method of treating a disease, the method comprising the administration of a tablet as defined herein to a patient/human in need thereof. In a preferred embodiment the disease treated is Parkinson's Disease where the active substance comprises or is ropinirole or another therapeutic agent for the treatment of this condition. According to such methods, especially with ropinirole, one or more multi-layer tablets can be administered once per day to the human need of such treatment, or a single multi-layer tablet can be administered once per day. The controlled-release ropinirole tablet of the

present invention is expected to be advantageous compared to the marketed ropinirole immediate-release (IR) formulation because it should allow a more constant and/or lower systemic concentration /  $C_{\max}$  over a 24-hr period, avoids the necessity with the IR tablet of taking ropinirole three times a day, and should avoid some of the side-effects which are possible when IR ropinirole is administered. See especially the advantageous approx. 24 hour *in vitro* release shown *inter alia* in ropinirole Examples 13-18 hereinafter: this is near-optimal for Parkinson's disease.

The invention also provides the use of a tablet as herein defined, wherein the active substance comprises or is ropinirole, in the manufacture of a medicament for the treatment of Parkinson's disease in a human. The invention also provides such a tablet for use in the treatment of Parkinson's disease.

Preferred features for the second and subsequent aspects of the invention are as for the first aspect *mutatis mutandis*.

The invention will now be further described by way of reference to the following Examples and Figures which are provided for the purposes of illustration only and are not to be construed as being limiting on the invention. Reference is made to a number of Figures in which:

FIGURE 1 shows a transverse section through a bilayer tablet in which the barrier layer is shown by hatching and the active substance containing layer by dots.

FIGURE 2 shows a transverse section through a trilayer tablet which has upper and lower barrier layers and a central active layer

FIGURE 3 shows a transverse section through a two-layer tablet, in which the barrier layer coats a lateral surface and the side of the active layer.

FIGURE 4 shows a transverse section through a two-layer tablet in which the

barrier layer is present as an annular ring around the active core.

FIGURE 5 shows a transverse section through a tablet of Figure 4 in which the active core consists of two different active layers.

5

FIGURE 6 shows a transverse section through a trilayer tablet in which the barrier layer (3) is superposed on active layer (2), which in turn is superposed on active layer (1).

10

FIGURE 7 shows a transverse section through a trilayer tablet in which the first active layer (5) is contained within barrier layer (6) and a second active layer (4).

15

FIGURE 8 shows a transverse section through a trilayer tablet in which the barrier layer (8) is present interposed between active layers (9) and (7).

20

FIGURE 9 shows plan, side elevation and end elevation views of a three layer caplet, in which an active substance layer (11) is interposed between barrier layers (10,12); a cross-sectional view is shown through line X--X.

25

FIGURE 10 shows a dissolution profiles of comparison, replication batches at dosages of 0.75mg ropinirole measured as effective free base to investigate the influence of coating on release - results shown for tablet P00K39E shown as "□", tablet P00K40E shown as "◇", tablet P00K41E shown as "△", tablet C511 shown as "■", tablet C519 shown as "◆", and tablet C529 shown as "▲". Results shown as percentage drug released (%) over time (hours).

30

FIGURE 11 shows a dissolution profiles of comparison, replication batches at dosages of 6mg ropinirole measured as effective free base to investigate the influence of coating on release - results shown for tablet P00K45E shown as "□", tablet P00K46E shown as "◇", tablet P00K47E shown as "△", tablet C530



shown as "■", tablet C531 shown as "◆", and tablet C532 shown as "▲".  
Results shown as percentage drug released (%) over time (hours).

FIGURE 12 shows a dissolution profiles of comparison, replication batches at  
dosages of 12mg ropinirole measured as effective free base to investigate the  
influence of coating on release - results shown for tablet P00K42E shown as  
"□", tablet P00K43E shown as "◇", tablet P00K44E shown as "△", tablet C512  
shown as "■", tablet C534 shown as "◆", and tablet C535 shown as "▲".  
Results shown as percentage drug released (%) over time (hours).

FIGURE 13 shows dosage influence on coated tablet displayed as a  
comparison of dissolution profiles of ropinirole at dosages of 0.75mg, 6mg and  
12mg measured as free base (results of replication batches). Results shown as  
percentage drug released (%) over time (hours), where tablets C511, C519 and  
C529 are 0.75mg ropinirole shown as "—", where tablets C530, C531 and  
C532 are 6mg ropinirole shown as "- - - - -", and where tablets C512, C534  
and C535 are 12mg ropinirole shown as "- - - - -".

**Example 1: Systems consisting of a single two-layer tablet - 4.0mg pindolol**

In Example 1, the first layer contains 4 mg of pindolol (slow release); the second layer  
consists of a "barrier" layer.

**1(a) Preparation of the granulate utilised for the preparation of the layer containing  
4.0 mg of slow release pindolol.**

Component	Amount (mg)
Pindolol	4.0 mg
Mannitol (C. Erba, Milan, I)	21.0 mg
Hydroxypropylmethylcellulose (HPMC) (Methocel® K 100 M, Colorcon, Orpington, UK)	63.0 mg (48 wt%)
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest, F)	35.0 mg
Polyvinylpyrrolidone (PVP) (Plasdone® K29-32, I.S.P.)	5.6 mg (4.2%)

Component	Amount (mg)
Magnesium stearate (C. Erba, Milan, I)	1.4 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	1.4 mg
Total	131.4 mg

In total, the active layer contains 52.2 weight % of gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC).

- 5 Mix pindolol, mannitol, hydroxypropylcellulose and glyceryl behenate, wet with an aqueous solution of 20% polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in a fluid-bed desiccator (Aeromatic mod. Strea) until constant weight is reached, pass over the same mesh sieve again. Add the lubricant and silica and mix in turbula for 10 minutes. In this way a granulate (granulate 1(a)) is obtained with good flow (slide) and compaction properties. The granulate is subjected to the compression stage as described later on.
- 10

1(b) Preparation of the granulate making up the second layer (barrier-layer)

Component	Amount
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	45.00%
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	25.00%
Lactose monohydrate	23.30%
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00%
Yellow iron oxide FCF aluminium lake (Colorcon, Orpington, UK)	0.18%
Carmine-indigo aluminium lake 20% (Colorcon, Orpington, UK)	0.12%
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00%
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.40%

- 15 Mix hydroxypropylmethylcellulose, glyceryl behenate and lactose, carefully disperse the dyes. Wet with an aqueous solution of 5% polyvinylpyrrolidone. Pass over a 25-

mesh sieve, desiccate in an oven (stove) at 30 °C for approximately 2 hours. Pass over the 25-mesh sieve again. Desiccate until constant weight is reached. Add the colloidal silica and magnesium stearate to the granulate obtained and mix in turbula for 15 minutes. In this way a granulate (granulate 1(b)) is obtained with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

#### 1(c) Preparation of the two-layer systems (by compression).

The granulates, obtained as previously quoted and according to well known models to all experts in the field, are loaded in the feedboxes of a rotary compressing machine suitable for producing multi-layer tablets (e.g. Manesty Layer-Press, Liverpool, UK). In particular, the granulate described in section 1(b) is loaded in the first; whereas the granulate as described in section 1(a) is loaded in the second feedbox. The compressing machine is equipped with 9 mm diameter circular concave punches.

The machine is set so as to produce two-layer systems consisting of an initial 100 mg of granulate barrier, a second layer of 131.4 mg containing the active principle (equal to 4.0 mg of pindolol.). Working as previously described, two-layer tablets are obtained with a mean weight of 231.4 mg, each containing 4.0 mg active principle. Table 1 contains the data relating to the release verification of the active principle from the tablets in Example 1.

#### Example 2: Systems consisting of a single two-layer tablet - 8.0mg pindolol

In Example 2, the first layer (slow release) contains 8 mg of pindolol; the second layer consists of a "barrier" layer.

A granulate is prepared as described in Example 1, in section 1(a), the only alteration being to double the amount of carried active principle. The second layer (barrier) is kept identical both qualitatively and quantitatively, as described in Example 1 in section 1(b). Working as described in section 1(c), two-layer tablets are prepared consisting of an initial amount of 100 mg of granulate barrier (barrier), a second layer of 135.4 mg containing the active principle (equal to 8.0 mg of pindolol). Hence two-

layer tablets are obtained with a mean weight of 235.4 mg, each containing 8.0 mg of active principle. Table 1 contains the data relating to the release verification of the active principle from the tablets in Example 2.

5     **Example 3: Systems consisting of a single two-layer tablet - 16.0mg pindolol**

In Example 3, the two-layer tablet system is as described in Examples 1 and 2 but containing 16.0 mg of pindolol.

10     A granulate is prepared as described in Example 1, in section 1(a), the only alteration being to carry 16 mg of active principle thus 143.4 mg of granulate contain 16.0 mg of pindolol. The second layer (barrier) is kept identical both qualitatively and quantitatively, as described in Example 1 in section 1(b). Working as described in section 1(c), two-layer tablets are prepared consisting of an initial amount of 100 mg of granulate barrier, a second layer of 143.4 mg containing the active principle (equal  
15     to 16.0 mg of pindolol). Hence two-layer tablets are obtained with a mean weight of 243.4 mg, each containing 16.0 mg of active principle. Table 1 contains the data relating to the release verification of the active principle from the tablets in Example 3.

20     **Example 4: Systems consisting of a single two-layer tablet - 24mg pindolol**

In Example 4, the two-layer tablet system is as described in Examples 1 and 2 but containing 24.0 mg of pindolol.

25     A granulate is prepared as described in Example 1, in section 1(a), the only alteration being to carry 24 mg of active principle; thus 151.4 mg of granulate contain 24.0 mg of pindolol. The second layer (barrier) is kept identical both qualitatively and quantitatively, as described in Example 1 in section 1(b). Working as described in section 1(c), two-layer tablets are prepared consisting of an initial amount of 100 mg of granulate barrier, a second layer of 151.4 mg containing the active principle (equal  
30     to 24.0 mg of pindolol). Hence two-layer tablets are obtained with a mean weight of 251.4 mg, each containing 24.0 mg of active principle. Table 1 contains the data relating to the release verification of the active principle from the tablets in Example 4.

**Example 5: Systems consisting of a single two-layer tablet - 32.0mg pindolol**

In Example 5, the two-layer tablet is as described in Examples 1 and 2 but containing 32.0 mg of pindolol.

- 5 A granulate is prepared as described in Example 1, in section 1(a), the only alteration being to carry 32.0 mg of active principle; thus 159.4 mg of granulate contain 32.0 mg of pindolol and 43 weight % of total gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC) or 40 wt % (more exactly 39.5 wt%) HPMC.
- 10 The second layer (barrier) is kept identical both qualitatively and quantitatively, as described in Example 1 in section 1(b). Working as described in section 1(c), two-layer tablets are prepared consisting of an initial amount of 100 mg of granulate barrier, a second layer of 159.4 mg containing the active principle (equal to 32.0 mg of pindolol). Hence two-layer tablets are obtained with a mean weight of 259.4 mg, each
- 15 containing 32.0 mg of active principle. Table 1 contains the data relating to the release verification of the active principle from the tablets in Example 5.

**Dissolution Test of Tablets Prepared in Examples 1 to 5**

- To assess the release characteristics of the active principle from the two-layer tablets, 20 quoted in Examples 1-5, equipment 2 is utilised, paddle (USP XXIII), working at 100 r.p.m. and utilising as dissolution fluid 900 mL of 0.1M hydrochloric acid at 37 °C.
- The release of the active principle is followed by HPLC assessment at 227 nm utilising an automatic sampling and reading system. The results of the experiments carried out are quoted in Table 1

25

Table 1

TIME (hours)	Percentage Released				
	Example 1	Example 2	Example 3	Example 4	Example 5
1	22.2	19.4	22.4	23.3	23.8
2	34.0	32.2	33.2	34.2	34.5

TIME (hours)	Percentage Released				
4	50.2	48.7	49.7	52.2	51.7
6	63.5	61.5	63.0	64.1	64.0
8	72.7	72.1	73.4	74.9	74.2
10	82.8	81.6	81.9	83.5	82.9
12	88.7	87.4	88.2	90.7	89.8
16	96.3	95.0	95.9	96.6	97.1
20	100.3	99.2	98.9	100.8	100.1

It is possible to point out that the release of the drug from the prepared systems is slowed down and the release of the whole drug takes approximately 20 hours. In addition, it is clear that the release kinetics are not substantially modified at any content level of active substance in the tablets. Such behaviour is in accordance with the present invention.

**Example 6: Systems consisting of a three-layer tablet - 4mg molsidomine**

In Example 6, a three-layer tablet is prepared in which the first layer consists of 80 mg of a "barrier" layer, the second layer (slow release) contains 4 mg of molsidomine; the third layer consists of 100 mg of a "barrier layer".

**6(a) Preparation of the granulate utilised for the preparation of the layer containing 4.0 mg of slow release molsidomine.**

Component	Amount (mg)
Molsidomine	4.00 mg
Mannitol (C Erba, Milan, I)	5.00 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	60.00 mg (63 wt%)
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	20.00 mg
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	3.70 mg

Component	Amount (mg)
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	1.63 mg
Total	95.33 mg

In total, the active layer contains 66.8 weight % (i.e. 67 wt%) of gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC).

5 Mix molsidomine, mannitol, hydroxypropylcellulose and glyceryl behenate, wet with a 20% solution of polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in a fluid-bed desiccator (Aeromatic mod. Strea) until constant weight is reached, pass over the same mesh sieve again. Add the silica and mix in a cubic mixer for 45 minutes, then add the magnesium stearate and mix for a further 15 minutes. In this way a granulate (granulate 6(a)) with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

6(b) Preparation of the granulate making up the barrier-layers.

Component	Amount
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	39.88%
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	13.50%
Lactose monohydrate	39.88%
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00%
Yellow iron oxide FCF (Sicovit Gelb 10-BASF Koln; D)	0.24%
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00%
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.50%
Total	100%

15 Mix hydroxypropylmethylcellulose, glyceryl behenate and lactose, carefully disperse the dye. Wet with a 5% aqueous solution of polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in an oven (stove) at 30 °C for approximately 2 hours. Pass over

a 25-mesh sieve again. Desiccate until constant weight is reached. Add the colloidal silica and magnesium stearate to the granulate obtained and mix in turbula for 15 minutes. In this way a granulate (granulate 6(b)) is obtained with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

6(c) Preparation of the three-layer systems (by compression).

The granulates, obtained as previously quoted and according to well known models to all experts in the field, are loaded in the feedboxes of a rotary compressing machine suitable for producing three-layer tablets (e.g. Manesty Layer-Press LP 39, Liverpool, UK). In particular, the granulate described in section 6(b) is loaded in the first and third feedboxes; whereas the granulate as described in section 6(a) is loaded in the second feedbox. The compressing machine is equipped with 8 mm diameter circular concave punches.

The machine is set so as to produce three-layer systems consisting of an initial 80.0 mg of granulate barrier, a second layer of 95.33 mg containing the active principle (equal to 4.0 mg of molsidomine) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 275.33 mg, each containing 4.0 mg active principle. Table 2 contains the data relating to the release verification of the active principle from the tablets in Example 6.

Example 7: Systems consisting of a single three-layer tablet - 8mg molsidomine

In Example 7, the first layer consists of 80 mg of a "barrier" layer, the second layer (slow release) contains 8 mg of molsidomine; the third layer consists of 100 mg of a "barrier" layer.

A granulate is prepared as described in Example 6, in section 6(a), the only alteration being to double the amount of carried active principle; such a granulate makes up the second layer of the three layer tablet. For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in



Example 6 in section 6(b). The compressing machine is equipped with 8 mm diameter circular concave punches.

The machine is set so as to produce three-layer systems consisting of an initial 80.0 mg of granulate barrier, a second layer of 99.33 mg containing the active principle (equal to 8.0 mg of molsidomine) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 279.33 mg, each containing 8.0 mg of active principle. Table 2 contains the data relating to the release verification of the active principle from the tablets in Example 7.

**Example 8: Systems consisting of a single three-layer tablet - 16 mg molsidomine**

In Example 8, the first layer consists of 80 mg of a "barrier" layer, the second layer (slow release) contains 16 mg of molsidomine; the third layer consists of 100 mg of a "barrier" layer. A granulate is prepared as described in Example 6, in section 6(a), the only alteration being to double the amount of carried active principle; such a granulate makes up the second layer of the three layer tablet.

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 6 in section 6(b). The compressing machine is equipped with 8 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 80.0 mg of granulate barrier, a second layer of 107.33 mg containing the active principle (equal to 16.0 mg of molsidomine) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 287.33 mg, each containing 16.0 mg of active principle. Table 2 contains the data relating to the release verification of the active principle from the tablets in Example 8.

**Example 9: Systems consisting of a single three-layer tablet - 20 mg molsidomine**

In Example 9, the first layer consists of 80 mg of a "barrier" layer, the second layer (slow release) contains 20 mg of molsidomine; the third layer consists of 100 mg of a "barrier" layer. A granulate is prepared as described in Example 6, in section 6(a), the only alteration being to double the amount of carried active principle; such a granulate

makes up the second layer of the three layer tablet. For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 6 in section 6(b). The compressing machine is equipped with 8 mm diameter circular concave punches.

5

The machine is set so as to produce three-layer systems consisting of an initial 80.0 mg of granulate barrier, a second layer of 111.33 mg containing the active principle (equal to 20.0 mg of molsidomine) and 57.2 weight % of gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC) or 54 wt% HPMC, and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 291.33 mg, each containing 20.0 mg of active principle. Table 2 contains the data relating to the release verification of the active principle from the tablets in Example 9.

10

#### 15 Dissolution Test of Tablets Prepared in Examples 6 to 9

To assess the release characteristics of the active principle from the three-layer tablets, quoted in Examples 6 to 9, equipment 2 is utilised, paddle (USP XXIII), working at 100 r.p.m. and utilising as dissolution fluid 900 mL of distilled water at 37 °C. The release of the active principle is followed by U.V. spectrophotometric assessment at 311 nm utilising an automatic sampling and reading system. The results of the experiments carried out are quoted in Table 2

20

Table 2

TIME (hours)	Percentage Released			
	Example 6	Example 7	Example 8	Example 9
1	12.3	11.4	11.9	12.6
2	19.6	20.7	18.8	21.2
4	32.7	33.8	31.5	33.0
6	41.5	43.0	42.5	43.1
8	52.8	54.2	53.0	54.5

TIME (hours)	Percentage Released			
10	64.0	66.5	65.3	63.6
12	74.7	76.4	75.2	77.0
16	88.4	89.6	86.8	89.8
20	96.5	98.0	95.9	96.6
24	100.3	102.3	99.4	101.8

It is possible to point out that the release of the drug from the prepared systems is slowed down and the release of the whole drug takes approximately 20 hours. In addition, it is clear that the release kinetics are not substantially modified at any content level of active substance in the tablets. Such behaviour is in accordance with the present invention.

**Example 10: Systems consisting of a single three-layer tablet - 0.1 mg of moxonidina**

In Example 10, the first layer consists of 100 mg of a "barrier" layer, the second layer (slow release) contains 0.1 mg of moxonidina; the third layer consists of 100 mg of a "barrier" layer.

**10(a) Preparation of the granulate utilised for the preparation of the layer containing 0.1 mg of slow release moxonidina.**

Component	Amount (mg)
Moxonidina	0.10 mg
Lactose monohydrate	29.90 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	50.00 mg (52 wt%)
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	10.00 mg
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00 mg
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00 mg

Component	Amount (mg)
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	1.00 mg
Total	97.00 mg

In total, the active layer contains 56.7 weight % of gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC).

5 Mix moxonidina, lactose, hydroxypropylcellulose and glyceryl behenate, wet with a solution of 20% polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in a fluid-bed desiccator (Aeromatic mod. Strea) until constant weight is reached, pass over the same mesh sieve again. Add the silica and mix in a cubic mixer for 45 minutes, then add the magnesium stearate and mix for a further 15 minutes. In this way a granulate (granulate 10(a)) is obtained with good slide and compaction properties. The  
10 granulate is subjected to the compression stage as described later on.

10(b) Preparation of the granulate making up the barrier-layers.

The composition and granulate described in Example 6(b) is utilised.

Component	Amount
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	39.88%
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest, F)	13.50%
Lactose monohydrate	39.88%
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00%
Yellow iron oxide FCF (Sicovit Gelb 10-BASF Köln; D)	0.24%
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00%
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.50%
Total	100.00%

15

Mix hydroxypropylmethylcellulose, glyceryl behenate and lactose and carefully disperse the dye. Wet with a 5% aqueous solution of polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in an oven (stove) at 30°C for approximately 2 hours. Pass over the 25-mesh sieve again. Desiccate until constant weight is reached. Add

the colloidal silica and magnesium stearate to the granulate obtained and mix in turbula for 15 minutes. In this way a granulate (granulate 10(b)) is obtained with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

5

10(c) Preparation of the three-layer systems (by compression).

The granulates obtained as previously quoted and according to well known models to all experts in the field, are loaded in the feedboxes of a rotary compressing machine suitable for producing three-layer tablets (e.g. Manesty Layer-Press LP 39, Liverpool, UK). In particular, the granulate described in section 10(b) is loaded in the first and third feedboxes; whereas the granulate as described in section 10(a) is loaded in the second feedbox. The compressing machine is equipped with 9 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 100.00 mg of granulate barrier, a second layer of 97.00 mg containing the active principle (equal to 0.10 mg of moxonidina.) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 297.00 mg, each containing 0.1 mg of active principle. Table 3 contains the data relating to the release verification of the active principle from the tablets in Example 10.

15  
20

Example 11: Systems consisting of a single three-layer tablet - 0.30mg moxonidina

In Example 11, the first layer consists of 100 mg of a "barrier" layer, the second layer (slow release) of 97.00 mg containing the active principle (equal to 0.30 mg of moxonidina); the third layer consists of 100 mg of a "barrier" layer.

25

11(a) Preparation of the granulate utilised for the preparation of the layer containing 0.3 mg of slow release moxonidina.

Component	Amount (mg)
Moxonidina	0.30 mg
Lactose monohydrate	29.70 mg

Component	Amount (mg)
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	50.00 mg
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	10.00 mg
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00 mg
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	1.00 mg
Total	97.00 mg

A granulate is prepared as described in Example 10, in section 10(a), the only alteration being to triple the amount of carried active principle; such a granulate makes up the second layer of the three-layer tablet.

5

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 6 in section 6(b). The compressing machine is equipped with 9.0 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 100.0 mg of granulate barrier, a second layer of 97.00 mg containing the active principle (equal to 0.3 mg of moxonidina) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 297.00 mg, each containing 0.3 mg of active principle. Table 3 contains the data relating to the release verification of the active principle from the tablets in Example 11.

10  
15

**Example 12: Systems consisting of a single three-layer tablet - 1.2 mg moxonidina**

In Example 12, the first layer consists of 100 mg of a "barrier" layer, the second layer (slow release) of contains 1.2 mg of moxonidina; the third layer consists of 100 mg of a "barrier" layer.

20

**12(a) Preparation of the granulate utilised for the preparation of the layer containing 1.2 mg of slow release moxonidina.**

Component	Amount (mg)
Moxonidina	1.20 mg
Lactose monohydrate	28.80 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	50.00 mg (52 wt%)
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	10.00 mg
Polyvinylpyrrolidone (Plasdone® K29-32, I.S.P.)	5.00 mg
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	1.00 mg
Total	97.00 mg

In total, the active layer contains 56.7 weight % of gellable, swellable and/or erodible hydrophilic polymers (PVP + HPMC).

A granulate is prepared as described in Example 11, in section 11(a), the only alteration being to quadruple the amount of carried active principle; such a granulate makes up the second layer of the three-layer tablet.

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 6 in section 6(b). The compressing machine is equipped with 9.0 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 100.0 mg of granulate barrier, a second layer of 97.00 mg containing the active principle (equal to 1.20 mg of moxonidina) and a third layer of 100.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 297.00 mg, each containing 1.20 mg of active principle. Table 3 contains the data relating to the release verification of the active principle from the tablets in Example 12.

#### **Dissolution Test of Tablets Prepared in Examples 10 to 12**

To assess the release characteristics of the active principle from the three-layer tablets, quoted in Examples 10-12, equipment 2 is utilised, paddle (USP XXIII), working at 100 r.p.m. and utilising as dissolution fluid 900 mL of distilled water at 37 °C. The release of the active principle is followed by HPLC assessment at 230 nm utilising an

automatic Hewlett-Packard system with a diode array detector. The results of the experiments carried out are quoted in Table 3.

Table 3

TIME (hours)	Percentage Released		
	Example 10	Example 11	Example 12
1	12.4	12.7	14.7
2	20.1	21.8	23.1
4	35.3	35.9	37.8
6	50.0	52.1	54.3
8	62.6	63.8	64.7
10	75.8	77.1	78.0
12	85.8	87.4	88.6
16	98.7	99.1	98.9
20	100.3	101.2	99.4

It is possible to point out that the release of the drug from the prepared systems is slowed down and the release of the whole drug takes approximately 20 hours. In addition, it is clear that the release kinetics are not substantially modified, even if the active substance content in the tablets varies by 120%. Such behaviour is in accordance with the present invention.

**Example 13: Systems consisting of a single three-layer tablet - 0.75mg ropinirole**

In Example 13, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 0.86 mg of Ropinirole HCl equal to 0.75 mg of base; the third layer consists of 120 mg of a "barrier" layer.

**13(a) Preparation of the granulate utilised for the preparation of the slow release base layer containing 0.86 mg of Ropinirole HCl equal to 0.75 mg of base.**



Component	Amount (mg)
Ropinirole HCl equal to 0.75 mg of base	0.86 mg
Hydroxypropylmethylcellulose (HPMC) (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg (41 wt%)
Sodium carboxymethylcellulose (NaCMC) (Blanose 9 M31XF)	15.00 mg (10 wt%)
Maltodextrin NF (Lycatab DSH)	7.50 mg (5 wt%)
Lactose (C. Erba, Milan, I)	47.74 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg (10 wt%)
Magnesium stearate (C. Erba, Milan, I)	1.50 mg (1 wt%)
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

In total, the active layer contains 51 weight % of the gellable, swellable and/or erodible hydrophilic polymers (HPMC + NaCMC), or 56 wt% if one includes maltodextrin.

5

Mix the Ropinirole and a part of the lactose for 20 minutes in a suitable mixer-granulator, (type Niro-Fielder PMA). Add the hydroxypropylmethylcellulose, sodium carboxymethylcellulose, hydrogenated castor oil, maltodextrin and the remainder of the lactose and mix for 10 minutes, wet with water (approx. 30% of the weight of the products utilised). The granulate obtained is desiccated in a fluid-bed desiccator (type Niro-Fielder TSG 2) until constant weight is reached. Pass over an 0.800 mm mesh sieve oscillating granulator again. Add the silica and mix in a cubic mixer for 20 minutes, then add the magnesium stearate and mix for a further 10 minutes. In this way a granulate (granulate 13(a)) is obtained with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

15

13(b) Preparation of the granulate making up the barrier-layers.

Component	Amount
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon,	44.76% (or

Component	Amount
Orpington, UK)	44.75%)
Mannitol (C. Erba)	23.60%
Glyceryl behenate (Compritol 888 Gattefossé, St. Priest; F)	25.00%
Polyvinylpyrrolidone (PVP) (Plasdone® K29-32, I.S.P.)	5.00%
Yellow iron oxide FCF (Sicovit Gelb 10-BASF Köln; D)	0.24% (or 0.25%)
Magnesium stearate (USP grade, C. Erba, Milan, I)	1.00%
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.40%
Total	100.00%

Mix hydroxypropylmethylcellulose, glyceryl behenate and mannitol and carefully disperse the dye. Wet with a 5% aqueous solution of polyvinylpyrrolidone. Pass over a 25-mesh sieve, desiccate in an oven (stove) at 30°C for approximately 2 hours. Pass over the 25-mesh sieve again. Desiccate until constant weight is reached. Add the colloidal silica and magnesium stearate to the granulate obtained and mix in turbula for 15 minutes. In this way a granulate (granulate 13(b)) is obtained with good slide and compaction properties. The granulate is subjected to the compression stage as described later on.

10

### 13(c) Preparation of the three-layer systems (by compression).

The granulates, obtained as previously quoted and according to well known models to all experts in the field, are loaded in the feedboxes of a rotary compressing machine suitable for producing three-layer tablets (e.g. Manesty Layer-Press LP 39, Liverpool, UK). In particular, the granulate described in section 13(b) is loaded in the first and third feedboxes; whereas the granulate as described in section 13(a) is loaded in the second feedbox. The compressing machine is equipped with a slightly concave 9 mm diameter circular punches.

The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing the active principle (0.86 mg of Ropinirole HCl equal to 0.75 mg of base) and a third layer of 120.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained

20

with a mean weight of 400.00 mg, each containing 0.86 mg of Ropinirole HCl, each equal to 0.75mg of base. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 13.

5     **Example 13A – variation of Example 13**

In an alternative embodiment to Example 13, the preparation of the granulate for the active layer 13(a) is done as follows:

10       Mix the HPMC, ropinirole, lactose, Na CMC, hydrogenated castor oil and maltodextrin for 6 minutes in a suitable mixer-granulator (type Niro Fielder PMA). Wet with water (approx. 30% of the weight of the products utilised). The granule obtained is desiccated in a fluid bed dryer (type Niro Fielder TSG 2) until the water content is between 1 and 4.5%. Pass through a 1.57 mm mesh sieve in a  
15       cone mill. Add silica and mix in a cubic mixer for 20 minutes, then add the magnesium stearate and mix for a further 2 minutes.

In this alternative embodiment, the preparation of the granulate for the barrier layer 13(b) is done as follows:

20       Mix the mannitol, the dye, the glyceryl behenate, the HPMC, and the PVP for 6 minutes in a suitable mixer-granulator (type Niro Fielder PMA). Wet with water (approx. 25% of the weight of the products utilised). The granule obtained is desiccated in a fluid bed dryer (type Niro Fielder TSG 2) until water content is  
25       between 1.1 and 2.7%. Pass through a 1.57 mm mesh sieve in a cone mill. Add silica and mix in a cubic mixer for 20 minutes, then add the magnesium stearate and mix for a further 2 minutes.

In further alternative embodiments, the above alternative procedures can also be used,  
30       *mutatis mutandis*, with the ingredients/formulations of any of the Examples 14 to 23 hereinafter.

**Example 14: Systems consisting of a single three-layer tablet - 1.00mg ropinirole**

In Example 14, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 1.14 mg of Ropinirole HCl equal to 1.00 mg of base; the third layer consists of 120 mg of a "barrier" layer.

A granulate is prepared as described in Example 13, in section 13(a), the only alteration being to increase the amount of carried active principle, reducing the lactose content by the same amount; such granulate makes up the second layer of the three-layer tablet.

14(a) Preparation of the granulate utilised for the preparation of the slow release layer containing 1.14 mg of Ropinirole HCl equal to 1.00 mg of base.

Component	Amount (mg)
Ropinirole HCl equal to 1.00 mg of base	1.14 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg
Sodium carboxymethylcellulose (Blanose 9 M31XF)	15.00 mg
Maltodextrin NF (Lycatab DSH)	7.50 mg
Lactose (C. Erba, Milan, I)	47.46 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg
Magnesium stearate (C. Erba, Milan, I)	1.50 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 13 in section 13(b). The compressing machine is equipped with slightly concave 9 mm diameter circular punches.

The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing 1.14 mg of Ropinirole HCl (equal to 1.00 mg of Ropinirole base) and a third layer of 120.0 mg of granulate

barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 400.00 mg, each containing 1.14 mg of Ropinirole HCl, equal to 1.00 mg of base. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 14.

5

**Example 15: Systems consisting of a single three-layer tablet - 3.00mg ropinirole**

In Example 15, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 3.42 mg of Ropinirole HCl equal to 3.00 mg of base; the third layer consists of 120 mg of "barrier" layer.

10

A granulate is prepared as described in Example 13, in section 13(a), the only alteration being to increase the amount of carried active principle, reducing the lactose content by the same amount; such granulate makes up the second layer of the three-layer tablet.

15

15(a) Preparation of the granulate utilised for the preparation of the slow release layer containing 3.42 mg of Ropinirole HCl equal to 3.00 mg of base.

Component	Amount (mg)
Ropinirole HCl equal to 3.00 mg of base	3.42 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg
Sodium carboxymethylcellulose (Blanose 9 M31XF)	15.00 mg
Maltodextrin NF (Lycatab DSH)	7.50 mg
Lactose (C. Erba, Milan, I)	45.18 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg
Magnesium stearate (C. Erba, Milan, I)	1.50 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

20

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 13 in section 13(b). The compressing

machine is equipped with slightly concave 9 mm diameter circular punches.

The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing 3.42 mg of Ropinirole HCl (equal to 3.00 mg of Ropinirole base) and a third layer of 120.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 400.00 mg, each containing 3.42 mg of Ropinirole HCl, each equal to 3.00 mg of base. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 15.

**Example 16: Systems consisting of a single three-layer tablet - 6.00mg ropinirole**

In Example 16, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 6.84 mg of Ropinirole HCl equal to 6.00 mg of base; the third layer consists of 120 mg of a "barrier" layer.

A granulate is prepared as described in Example 13, in section 13(a), the only alteration being to increase the amount of carried active principle, reducing the lactose content by the same amount; such granulate makes up the second layer of the three-layer tablet.

16(a) Preparation of the granulate utilised for the preparation of the slow release layer containing 6.84 mg of Ropinirole HCl equal to 6.00 mg of base.

Component	Amount (mg)
Ropinirole HCl equal to 6.00 mg of base	6.84 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg
Sodium carboxymethylcellulose (Blanose 9 M31XF)	15.00 mg
Maltodextrin NF (Lycatab DSH)	7.50 mg
Lactose (C. Erba, Milan, I)	41.76 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg

Component	Amount (mg)
Magnesium stearate (C. Erba, Milan, I)	1.50 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 13 in section 13(b). The compressing machine is equipped with slightly concave 9 mm diameter circular punches. The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing 6.84 mg of Ropinirole HCl (equal to 6.00 mg of Ropinirole base) and a third layer of 120.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 400.00 mg, each containing 6.84 mg of Ropinirole HCl, equal to 6.00 mg of base. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 16.

**Example 17: Systems consisting of a single three-layer tablet - 9.00mg ropinirole**

In Example 17, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 10.26 mg of Ropinirole HCl equal to 9.00 mg of base; the third layer consists of 120 mg of a "barrier" layer.

A granulate is prepared as described in Example 13, in section 13(a), the only alteration being to increase the amount of carried active principle, reducing the lactose content by the same amount; such granulate makes up the second layer of the three-layer tablet.

**17(a) Preparation of the granulate utilised for the preparation of the slow release layer containing 10.26 mg of Ropinirole HCl equal to 9.00 mg of base.**

Component	Amount (mg)
Ropinirole HCl equal to 9.00 mg of base	10.26 mg

Component	Amount (mg)
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg
Sodium carboxymethylcellulose (Blanose 9 M31XF)	15.00 mg
Maltodextrin NF (Lycatab DSH)	7.50 mg
Lactose (C. Erba, Milan, I)	38.34 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg
Magnesium stearate (C. Erba, Milan, I)	1.50 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 13 in section 13(b). The compressing machine is equipped with 8 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing the active principle (equal to 9.00 mg of Ropinirole base) and a third layer of 120.0 mg of granulate barrier. Working as previously described, three-layer tablets are obtained with a mean weight of 400.00 mg, each containing 9.00 mg of active principle. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 17.

**Example 18: Systems consisting of a single three-layer tablet - 12.00mg ropinirole**

In Example 18, the first layer consists of 130 mg of a "barrier" layer, the second layer (slow release) contains 13.68 mg of Ropinirole HCl equal to 12.00 mg of base; the third layer consists of 120 mg of a "barrier" layer.

A granulate is prepared as described in Example 13, in section 13(a), the only alteration being to increase the amount of carried active principle, reducing the lactose content by the same amount; such granulate makes up the second layer of the three-layer tablet.

**18(a) Preparation of the granulate utilised for the preparation of the slow release layer**



containing 13.68 mg of Ropinirole HCl equal to 12.00 mg of base.

Component	Amount (mg)
Ropinirole HCl equal to 12.00 mg of base	13.68 mg
Hydroxypropylmethylcellulose (Methocel® K 100 M, Colorcon, Orpington, UK)	61.50 mg
Sodium carboxymethylcellulose (Blanose 9 M31XF)	15.00 mg
Maltodextrin NF (Lycatab DSH)	7.50 mg
Lactose (C. Erba, Milan, I)	34.92 mg
Hydrogenated castor oil (Cutina HR-Henkel, D)	15.00 mg
Magnesium stearate (C. Erba, Milan, I)	1.50 mg
Colloidal silica (Syloid 244, Grace GmbH, Worms, D)	0.90 mg
Total	150.00 mg

For the first and third layer (barrier) a qualitatively and quantitatively identical granulate is employed, as described in Example 13 in section 13(b). The compressing machine is equipped with 8 mm diameter circular concave punches. The machine is set so as to produce three-layer systems consisting of an initial 130.0 mg of granulate barrier, a second layer of 150 mg containing the active principle (equal to 12.00 mg of Ropinirole base) and a third layer of 120.0 mg of granulate barrier. Working as described previously, three-layer tablets are obtained with a mean weight of 400.00 mg, each containing 12.00 mg of the active principle. Table 4 contains the data relating to the release verification of the active principle from the tablets in Example 18.

#### **Dissolution Test of Tablets Prepared in Examples 13 to 18**

To assess the release characteristics of the active principle from the three-layer tablets, quoted in Examples 13-18, equipment 2 is utilised, paddle (USP XXIII), working at 100 r.p.m. and utilising as dissolution fluid 500 mL of aqueous buffer solution of citrate (pH4.0), at 37 °C. The release of the active principle is followed by HPLC assessment at 250 nm utilising an automatic sampling and reading system. The results of the experiments carried out are quoted in Table 4.

Table 4

TIME (hours)	Percentage Released in Tablets of Examples 13 to 18 (Ex. 13 to Ex.18)					
	Ex. 13	Ex. 14	Ex. 15	Ex.16	Ex. 17	Ex. 18
1	7.3	8.6	7.8	7.5	8.8	9.4
2	12.1	12.6	12.0	13.4	13.5	14.0
4	18.9	21.0	19.5	20.7	22.1	23.9
6	26.0	28.5	27.9	28.5	29.8	33.1
9	38.3	39.7	39.2	40.3	41.2	44.9
12	49.6	51.4	50.7	51.0	52.6	56.7
16	67.8	66.9	64.5	66.3	66.4	70.0
20	82.0	81.3	78.4	79.5	80.3	80.1
24	90.4	91.3	88.9	89.1	88.7	91.2

It is possible to point out that the release of the drug from the prepared systems is slowed down and the release of most of the drug takes approximately 24 hours.

In addition, it is clear that the release kinetics are not substantially modified at any content of active substance in the tablets. Such behaviour is in accordance with the present invention.

#### **Example 19: Preparation of Ropinirole Round Tablet Formula**

Tablet formulations of ropinirole as a round tablet were prepared as follows. The tablet comprised an upper support or barrier layer (1), an active layer (2) and a lower support or barrier layer (3). HPMC is an abbreviation for hydroxypropylmethylcellulose.

#### **Support Layer (1)**

Component	Role	Amount mg/tablet

Component	Role	Amount mg/tablet
HPMC type 2208 / K 100M (100,000 cps)	Hydrophilic matrix polymer	58.18
Mannitol	Filler, Diluent	30.68
Glyceryl behenate	Hydrophobic compound	32.50
Polyvinylpyrrolidone (Povidone)	Binder	6.50
Magnesium stearate	Lubricant	1.30
Colloidal silicon dioxide	Glidant	0.52
Yellow ferric oxide	Colouring agent	0.33
Purified water	Granulation liquid	b
Total		130.00

### Active Layer (2)

Described in terms of three tablet strength formulations of ropinirole at 0.75mg, 1mg or 3mg per tablet ropinirole measured as effective base present.

Component	Role	Amount mg/tablet		
		0.75mg	1mg	3mg
Ropinirole HCl	Active Substance	0.855	1.14	3.42
Lactose monohydrate	Filler, diluent	47.745	47.46	45.18
HPMC type 2208 / K 100M (100,000 cps)	Hydrophobic matrix polymer	61.50 (41 wt%)	61.50	61.50
Carboxymethylcellulose sodium	Viscosity regulating agent	15.00	15.00	15.00
Maltodextrin	Binder	7.50	7.50	7.50
Hydrogenated castor oil	Hydrophobic compound	15.00	15.00	15.00
Magnesium stearate	Lubricant	1.50	1.50	1.50
colloidal silicon dioxide	Glidant	0.90	0.90	0.90
Purified water	Granulation liquid	b	b	b
Total		150.00	150.00	150.00

### Support Layer (3)

Component	Role	Amount mg/tablet
HPMC type 2208 / K 100M (100,000 cps)	Hydrophilic matrix polymer	53.70
Mannitol	Filler, Diluent	28.32
Glyceryl behenate	Hydrophobic compound	30.00
Polyvinylpyrrolidone (Povidone)	Binder	6.00
Magnesium stearate	Lubricant	1.20
Colloidal silicon dioxide	Glidant	0.48
Yellow ferric oxide	Colouring agent	0.30
Purified water	Granulation liquid	b
Total		120.00

The purified water included as granulation liquid does not remain in the finished product as indicated by the reference sign "b".

#### 5 **Example 20: Preparation of Ropinirole Caplet Formula**

Tablet formulations of ropinirole as a caplet were prepared as follows. The tablet comprised an upper support or barrier layer (1), an active layer (2) and a lower support or barrier layer (3), as shown in Figure 9 (in which reference numerals 10,12 represent the barrier layers and 11 the active layer). HPMC is an abbreviation for hydroxypropylmethylcellulose. Described in terms of four tablet strength formulations of ropinirole at 1mg, 3mg, 6mg, 9mg or 12mg per tablet ropinirole measured as effective base present.

#### **Support layer (1)**

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer	76.07	76.07	76.07	76.07
Mannitol	Filler, diluent	40.12	40.12	40.12	40.12
Glyceryl behenate	Hydrophobic compound	42.50	42.50	42.50	42.50

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
Polyvinylpyrrolidone (Povidone)	Binder	8.50	8.50	8.50	8.50
Magnesium stearate	Lubricant	1.70	1.70	1.70	1.70
Colloidal silicon dioxide	Glidant	0.68	0.68	0.68	0.68
Yellow ferric oxide	Colouring agent	0.43	0.43	0.43	0.43
Purified water	Granulation liquid	c	c	c	c
Total		170.00	170.00	170.00	170.00

**Active layer (2)**

Component	Role	Amount ropinirole (mg/tablet)				
		1mg	3mg	6mg	9mg	12mg
Ropinirole HCl	Active substance	1.14	3.42	6.84	10.26	13.68
Lactose monohydrate	Filler, diluent	47.46	45.18	41.76	38.34	34.92
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer (41 wt%)	61.50	61.50	61.50	61.50	61.50
Carboxymethyl- cellulose sodium	Viscosity regulating agent	15.00	15.00	15.00	15.00	15.00
Maltodextrin	Binder	7.50	7.50	7.50	7.50	7.50
Hydrogenated castor oil	Hydrophobic compound	15.00	15.00	15.00	15.00	15.00
Magnesium stearate	Lubricant	1.50	1.50	1.50	1.50	1.50
Colloidal silicon dioxide	Glidant	0.90	0.900	0.90	0.90	0.90
Purified water	Granulation liquid	c	c	c	c	c
Total		150.00	150.00	150.00	150.00	150.00

**Support layer (3)**

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer	62.65	62.65	62.65	62.65

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
Mannitol	Filler, diluent	33.04	33.04	33.04	33.04
Glyceryl behenate	Hydrophobic compound	35.00	35.00	35.00	35.00
Polyvinylpyrrolidone (Povidone)	Binder	7.00	7.00	7.00	7.00
Magnesium stearate	Lubricant	1.40	1.40	1.40	1.40
Colloidal silicon dioxide	Glidant	0.56	0.56	0.56	0.56
Yellow ferric oxide	Colouring agent	0.35	0.35	0.35	0.35
Purified water	Granulation liquid	c	c	c	c
Total		140.00	140.00	140.00	140.00

### Film coating

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
OPADRY OY-S-28876 WHITE	Coating agent	13.80	13.80	13.80	13.80
Purified water	Coating liquid	c	c	c	c
Total tablet weight (layers 1, 2, 3 and coat)		473.80	473.80	473.80	473.80

5 The purified water included as granulation liquid or coating liquid does not remain in the finished product as indicated by the reference sign "c". OPADRY OY-S-28876 WHITE is 63% HPMC 2910 6cP, 7% PEG 400, 30% TiO<sub>2</sub>. Red/pink (0.01-0.25%) and/or yellow (0.1 to 1.5%) colourings can also be added (iron oxides), the HPMC varying between 61-66%. An alternative blue coating uses 31-32% each of HPMC 2910 3cP and HPMC 2910 5cP, 8% PEG400, 23-24% TiO<sub>2</sub>, 1% polysorbate, and  
10 indigotine as blue dye at 4-5%.

### Example 21: Preparation of Ropinirole Caplet Formula

Tablet formulations of ropinirole as a caplet were prepared as follows. The tablet comprised an upper support or barrier layer (1), an active layer (2) and a lower support

or barrier layer (3), as with example 20. Described in terms of four tablet strength formulations of ropinirole at 1mg, 3mg, 6mg, 9mg and 12 mg per tablet ropinirole measured as effective base present. This example is the same as Example 20 but the yellow ferric oxide in the support or barrier layers are absent.

5

**Support layer (1)**

Component	Role	Amount ropinirole (mg/tablet)
		1, 3 or 6 mg
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer	76.50
Mannitol	Filler, diluent	40.12
Glyceryl behenate	Hydrophobic compound	42.50
Polyvinylpyrrolidone (Povidone)	Binder	8.50
Magnesium stearate	Lubricant	1.70
Colloidal silicon dioxide	Glidant	0.68
Purified water	Granulation liquid	d
Total		170.00

**Active layer (2)**

Component	Role	Amount ropinirole (mg/tablet)				
		1mg	3mg	6mg	9mg	12mg
Ropinirole HCl	Active substance	1.14	3.42	6.84	10.26	13.68
Lactose monohydrate	Filler, diluent	47.46	45.18	41.76	38.34	34.92
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer	61.50 (41 wt%)	61.50	61.50	61.50	61.50
Carboxymethyl- cellulose sodium	Viscosity regulating agent	15.00	15.00	15.00	15.00	15.00
Maltodextrin	Binder	7.50	7.50	7.50	7.50	7.50
Hydrogenated castor oil	Hydrophobic compound	15.00	15.00	15.00	15.00	15.00
Magnesium stearate	Lubricant	1.50	1.50	1.50	1.50	1.50
Colloidal silicon dioxide	Glidant	0.90	0.900	0.90	0.90	0.90
Purified water	Granulation liquid	c	c	c	c	c
Total		150.00	150.00	150.00	150.00	150.00

**Support layer (3)**

Component	Role	Amount ropinirole (mg/tablet)
		1, 3 or 6 mg
HPMC type 2208 (100,000 cps)	Hydrophilic matrix polymer	63.00
Mannitol	Filler, diluent	33.04
Glyceryl behenate	Hydrophobic compound	35.00
Polyvinylpyrrolidone (Povidone)	Binder	7.00
Magnesium stearate	Lubricant	1.40
Colloidal silicon dioxide	Glidant	0.56
Purified water	Granulation liquid	d
Total		140.00

**Film coating**

Component	Role	Amount ropinirole (mg/tablet)			
		1mg	3mg	6 or 9 mg	12mg
OPADRY OY-S-28876 WHITE	Coating agent	13.80	13.80	13.80	13.80
Purified water	Coating liquid	d	d	d	d
Total tablet weight (layers 1, 2, 3 and coat)		473.80	473.80	473.80	473.80

5

The purified water included as granulation liquid or coating liquid does not remain in the finished product as indicated by the reference sign "d".

**Examples 22 and 23: Preparation of Ropinirole Caplet Formula**

10

Tablet formulations of ropinirole as a caplet were prepared as follows. The tablet comprised an upper support or barrier layer (1), an active layer (2) and a lower support or barrier layer (3), as for Examples 20 and 21. Example formulations 22 and 23 are described as a single tablet strength formulation each of ropinirole at 0.75mg per tablet ropinirole measured as effective base present (0.855mg measured as the HCl salt). As

15

can be seen, Examples 22 and 23 involve identical active layers to the 0.75mg



ropinirole active layer of Example 19, but different barrier layers to Example 19, with different amounts and grades of HPMC in the barrier layers, replacement of mannitol with lactose, and lower amounts of glyceryl behenate. As can be seen, Examples 22 and 23 have 10% and 40 weight % respectively of K4M HPMC in their barrier layers which gives a slightly faster release profile *in vitro* than the ca. 45 wt% K100M HPMC present in the barrier layers of Examples 13-18 and 19-21, as *inter alia* the ropinirole migrates faster through the barrier layers. Example 22 has 20 wt % of K100LV HPMC as well as 10 wt % K4M HPMC in the barrier layer - the low-viscosity (LV) HPMC in the barrier layer may increase water uptake and aid gelling, increasing the matrix viscosity and decreasing the release rate.

#### Support layer (1) for Examples 22,23

Component	Role	Amount (mg/tablet)	
		Example 22	Example 23
HPMC K 4M	Hydrophilic matrix polymer	13.00	51.84
HPMC K100LV	Hydrophilic matrix polymer	26.00	
Lactose monohydrate		64.68	51.84
Glyceryl behenate	Hydrophobic compound	17.56	17.55
Polyvinylpyrrolidone (Povidone)	Binder	6.50	6.50
Magnesium stearate	Lubricant	1.30	1.30
Colloidal silicon dioxide	Glidant	0.64	0.63
Yellow ferric oxide	Colouring agent	0.32	0.32
Purified water	Granulation liquid	c	c
Total		130.00	130.00

#### Active Layer (2) for Examples 22 and 23

Described in terms of three tablet strength formulations of ropinirole at 0.75mg per tablet ropinirole measured as effective base present.

Component	Role	Amount ropinirole mg/tablet
		0.75mg
Ropinirole HCl	Active Substance	0.855
Lactose monohydrate	Filler, diluent	47.745
HPMC type 2208 / K 100M (100,000 cps)	Hydrophobic matrix polymer	61.50
Carboxymethylcellulose sodium	Viscosity regulating agent	15.00
Maltodextrin	Binder	7.50
Hydrogenated castor oil	Hydrophobic compound	15.00
Magnesium stearate	Lubricant	1.50
Colloidal silicon dioxide	Glidant	0.90
Purified water	Granulation liquid	c
Total		150.00

## Support layer (3) for Examples 22, 23

Component	Role	Amount (mg/tablet)	
		Example 22	Example 23
HPMC K4M	Hydrophilic matrix polymer	12.00	47.86
HPMC K100LV		24.00	
Lactose monohydrate		59.70	47.86
Glyceryl behenate	Hydrophobic compound	16.20	16.20
Polyvinylpyrrolidone (Povidone)	Binder	6.00	6.00
Magnesium stearate	Lubricant	1.20	1.20
Colloidal silicon dioxide	Glidant	0.60	0.60
Yellow ferric oxide	Colouring agent	0.30	0.30
Purified water	Granulation liquid	c	c
Total		120.00	120.00

The purified water included as granulation liquid or coating liquid does not remain in the finished product as indicated by the reference sign "c".

Note: The active layer for each Example 22 and 23 above can be replaced by the active layers of examples 20 and 21 using 1mg, 3mg, 6mg, 9mg and 12mg ropinirole measured as effective base present.

5

Note: in all the ropinirole examples 13-18 and 19-23, higher doses of up to 24 mg ropinirole per day can be administered by e.g. 2 x 12 mg tablets. Other doses e.g. 4 mg per day can be administered using 1 x 1 mg and 1 x 3 mg tablet per day. Also, in any of the Examples 13-23, different doses of for example 0.25 mg, 0.5 mg and 2 mg ropinirole can be used in the active layer by varying the amount of lactose while keeping the total weight of the active layer constant.

10

**Example 24: Further studies on caplet preparation and drug dissolution profiles**

The following further studies on caplet preparation are presented to show drug dissolution profiles for ropinirole caplets containing 0.75mg, 6mg or 12mg ropinirole measured as effective base present.

15

Formulation of Ropinirole HCl CR caplet, detailed per layer, mg/tablet			
Ingredients			
<i>Layer 1, support layer D14-4 Yellow</i>			
HPMC type 2208 (100 000 cps)	76.075		
Mannitol	40.120		
Glyceryl behenate	42.500		
Povidone	8.500		
Yellow ferric oxide	0.425		
Magnesium stearate vegetable	1.700		
Colloidal silicon dioxide	0.680		
Purified water	a		
Total	170.000		
<i>Layer 2, active layer</i>	<i>0.75 mg</i>	<i>6 mg</i>	<i>12 mg</i>
Ropinirole HCl	0.855	6.840	13.680
Lactose monohydrate	47.745	41.760	34.920
HPMC type 2208 (100 000 cps)	61.500	61.500	61.500
Carboxymethylcellulose sodium	15.000	15.000	15.000
Maltodextrin	7.500	7.500	7.500
Hydrogenated castor oil	15.000	15.000	15.000

Formulation of Ropinirole HCl CR caplet, detailed per layer, mg/tablet			
Ingredients			
Magnesium stearate vegetable	1.500	1.500	1.500
Colloidal silicon dioxide	0.900	0.900	0.900
Purified water	a	a	a
Total, layer 2	150.000	150.000	150.000
Layer 3, support layer D14-4 Yellow			
HPMC type 2208 (100 000 cps)		62.650	
Mannitol		33.040	
Glyceryl behenate		35.000	
Povidone		7.000	
Yellow ferric oxide		0.350	
Magnesium stearate vegetable		1.400	
Colloidal silicon dioxide		0.560	
Purified water		a	
Total		140.000	
Film coating			
OPADRY OY-S-28876 WHITE		13.800	
Purified water		a	
Total, tablet		473.800	

Notes:

a = Does not remain in the final product

5

0.855mg of Ropinirole HCl is corresponding to 0.75mg of Ropinirole Base

6.840mg of Ropinirole HCl is corresponding to 6.00mg of Ropinirole Base

13.680mg of Ropinirole HCl is corresponding to 12.00mg of Ropinirole Base

10

The drug release profiles were measured using standard techniques. The results were as follows (results presented in terms of percentage drug released at given time intervals in hours):

Analytical results						
Dosage, mg	0.75	0.75	0.75	6	6	6
Batch no.	C511	C519	C529	C530	C531	C532
Tablet	P00K41E	P00K40E	P00K39E	P00K45E	P00K46E	P00K47E
Tablet weight, mg	471.95	472.32	472.08	474.08	471.50	473.37
Tablet wt RSD, %	0.78	1.44	0.65	0.98	1.10	1.08

Analytical results						
Dosage, mg	0.75	0.75	0.75	6	6	6
Time, h						
0.00	0.00	0.00	0.00	0.00	0.00	0.00
1.00	8.96	6.88	7.43	8.67	8.20	8.71
2.00	12.42	11.45	11.69	13.47	13.17	13.48
4.00	19.99	19.93	19.59	22.03	22.01	21.55
6.00	27.45	27.62	27.43	30.21	29.65	30.17
9.00	38.24	38.60	38.34	41.68	41.46	41.81
12.00	49.78	49.58	50.00	52.07	52.36	52.33
16.00	64.53	64.48	65.47	66.17	66.41	66.26
20.00	77.17	76.98	78.68	78.01	78.34	78.72
24.00	85.79	86.17	88.18	87.09	87.69	88.19
30.00	92.40	93.57	95.40	95.26	94.81	95.41
36.00	94.37	96.00	97.19	97.96	97.17	97.58

Analytical results			
Dosage, mg	12	12	12
Batch no.	C512	C534	C535
Tablet	P00K42E	P00K43E	P00K44E
Tablet weight, mg	470.39	473.62	474.78
Tablet weight RSD, %	0.93	1.28	1.02
Time, h			
0.00	0.00	0.00	0.00
1.00	9.45	10.10	9.73
2.00	14.87	15.53	15.23
4.00	24.37	24.87	24.55
6.00	33.38	33.74	33.33
9.00	45.56	46.22	45.81
12.00	56.81	57.40	56.71
16.00	69.54	70.90	69.52
20.00	80.95	81.64	79.95
24.00	89.07	89.76	88.12
30.00	95.76	96.63	94.60
36.00	97.80	99.38	97.26

CLAIMS

1. A multi-layer controlled-release tablet comprising:
  - 5 (a) one active layer containing: (i) an active substance, (ii) hydrophilic polymeric substances which swell and/or gel and/or erode upon contact with aqueous liquids, (iii) lipophilic substances, and (iv) adjuvant substances, wherein the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in said active layer is in the range of 10:1 to  
10 0.5:1; and
  - (b) one or more barrier layers containing one or more of: hydrophilic polymeric substances which swell and/or gel and/or erode upon contact with aqueous liquids, lipophilic substances, and adjuvant substances.
- 15 2. A multi-layer tablet as claimed in claim 1, in which the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in said active layer is in the range of 7:1 to 1:1
- 20 3. A multi-layer tablet as claimed in claim 1 or claim 2, in which said hydrophilic polymeric substances (ii) are contained in a percentage between 1% and 75%, preferably between 5% and 65%, of the weight of the active layer.
- 25 4. A multi-layer tablet as claimed in any one of claims 1 to 3, in which said lipophilic substances (iii) are contained in a percentage between 1% and 70%, preferably between 5 and 55% of the weight of said active layer.
- 30 5. A multi-layer tablet as claimed in any one of claims 1 to 4, in which said adjuvants (iv) are contained in a percentage between 5% to 50%, preferably from 10% to 40%, of the weight of said active layer.
6. A multi-layer tablet as claimed in any one of claims 1 to 5, in which the weight

ratio between said active substance (i) and said adjuvant substances (iv) in the active layer is in the range of 0.001:1 to 4:1, preferably from 0.003:1 to 3:1.

7. A multi-layer tablet as claimed in any preceding claim, in which said one or more barrier layers are applied to one or both surfaces (bases) of the active layer.

8. A multi-layer tablet as claimed in any preceding claim, in which the weight ratio of hydrophilic swelling and/or gelling and/or erodible polymeric substances to lipophilic substances contained in the barrier layer is in the range of 1:1 to 7.5:1, suitably, from 1.5:1 to 4:1, and preferably between 2:1 and 3.5:1.

9. A multi-layer tablet as claimed in any preceding claim, in which the active substance (i) is contained in a weight percentage between 0.01% to 70%, preferably between 0.05% to 50% by weight of the active layer.

10. A multi-layer tablet as claimed in claim 9, in which the active substance (i) is contained in a percentage of 0.05% to 20% by weight of the active layer.

11. A multi-layer tablet as claimed in any preceding claim, in which the active layer contains polymeric material with slow swelling and/or gelification and/or erosion and/or solubility properties.

12. A multi-layer tablet as claimed in any preceding claim, in which the active layer further contains polymeric substances of a lipophilic nature.

13. A multi-layer tablet as claimed in any preceding claim, in which said hydrophilic polymeric substances comprise a pharmaceutically acceptable biocompatible and/or biodegradable material, including non-cross-linked polyvinylpyrrolidone, hydroxypropylcellulose with a molecular weight of 100,000 to 4,000,000, sodium carboxymethylcellulose, carboxymethylstarch, potassium methacrylate-divinylbenzene copolymer, hydroxypropylmethylcellulose of molecular weight between 2,000 and 4,000,000, a polyethyleneglycol of molecular weight

between 200 and 15,000, a polyoxyethylene with molecular weight of up to 20,000,000, a carboxyvinylpolymer, a poloxamer (polyoxyethylene-polyoxypropylene copolymer), a polyvinylalcohol, a glucane(glucan), a carrageenan, a scleroglucane (scleroglucan), a mannan, a galactomannan, gellans, xanthans, alginic acid and/or a derivative thereof, polyaminoacids, methyl vinyl ether / maleic anhydride copolymer, carboxymethylcellulose and/or a derivative thereof, ethylcellulose, methylcellulose, starch, a starch derivative, alpha, beta, or gamma cyclodextrin and/or a dextrin derivative.

14. A multi-layer tablet as claimed in any preceding claim, in which said lipophilic substances include a natural fat (for example coconut, soya, cocoa) as such or totally or partially hydrogenated, beeswax, polyethoxylated beeswax, a mono-, bi- or tri-substituted glyceride, glyceryl palmitostearate, glyceryl behenate, diethyleneglycol palmitostearate, a polyethyleneglycol stearate, a polyoxyethyleneglycol palmitostearate, glyceryl monopalmitostearate, cetyl palmitate, polyethyleneglycol palmitostearate, mono- or di-glyceryl behenate, a fatty alcohol associated with a polyethoxylate fatty alcohol, cetyl alcohol, stearic acid, a saturated or unsaturated fatty acid or a hydrogenated derivative thereof, and/or hydrogenated castor oil.

15. A multi-layer tablet as claimed in any preceding claim, in which the active substance(s) are therapeutic agents for the treatment of chronic diseases, for example drugs acting on the cardiovascular system, anti-arrhythmics, cardiac stimulants, vasodilators, anti-hypertensives, anti-adrenergic substances of central and peripheral action or substances acting on the arteriolar musculature, substances acting on the renin-angiotensin system, anti-hypertensives and diuretics in association, anti-Parkinson's Disease agents, diuretics and drugs for the treatment of Alzheimer's disease.

16. A multi-layer tablet as claimed in any preceding claim, in which the active substance(s) is selected from: propranolol, atenolol, pindolol, ropinirole, prazosin, ramipril, spirapril; spironolactone, metipranolol, molsidomine, moxonidina, nadolol,



nadexolol, levodopa, metoprolol, or timolol, inclusive of pharmaceutically acceptable salts thereof.

17. A multi-layer tablet as claimed in any preceding claim, in which the tablet preparation is carried out by compression of the powder or granular mixture and working between 1000 and 5000 Kg/cm<sup>2</sup>.

18. A multi-layer tablet as claimed in any preceding claim, in which the lipophilic substance present in the active layer is selected from hydrogenated castor oil and glyceryl behenate.

19. A multi-layer tablet as claimed in any preceding claim, in which the active substance comprises or is ropinirole, inclusive of pharmaceutically acceptable salts thereof.

20. A multi-layer tablet as claimed in claim 19, in which the amount of ropinirole present, inclusive of pharmaceutically acceptable salts thereof, is up to 12.0mg, measured as the amount of ropinirole base present.

21. A multi-layer tablet as claimed in claim 19, in which the amount of ropinirole present, inclusive of pharmaceutically acceptable salts thereof, is from 0.75mg to 12.0mg, measured as the amount of ropinirole base present.

22. A multi-layer tablet as claimed in any preceding claim, in which the active layer consists of components (i) to (iv) wherein the active substance is contained in a percentage of 0.05% to 20% by weight of the active layer, the adjuvant substances are contained in a percentage of 5% to 50% by weight of the active layer, and the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in the active layer is in the range of from 7:1 to 1:1.

23. A multi-layer tablet as claimed in any preceding claim, in which the active layer consists essentially of components (i) to (iv) wherein the active substance is

contained in a percentage of 0.05% to 20% by weight of the active layer, the adjuvant substances are contained in a percentage of 5% to 50% by weight of the active layer, and the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in the active layer is in the range of from 7:1 to 1:1.

5

24. A multi-layer tablet as claimed in any preceding claim, in which the hydrophilic polymeric substance comprises hydroxypropylmethylcellulose of molecular weight 2,000 to 4,000,000, sodium carboxymethylcellulose or calcium carboxymethylcellulose.

10

25. A multi-layer tablet as claimed in any preceding claim, in which (i) the active substance is ropinirole contained in a percentage of 0.05% to 20% by weight of the active layer, (ii) the hydrophilic polymeric substance comprises hydroxypropylmethylcellulose, sodium carboxymethylcellulose or calcium carboxymethylcellulose, (iii) the lipophilic substance comprises hydrogenated castor oil or glyceryl behenate, and (iv) the adjuvant substances are contained in a percentage of 5% to 50% by weight of the active layer, and the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in the active layer is in the range of from 7:1 to 1:1.

20

26. A multi-layer tablet as claimed in any preceding claim, wherein the active substance is ropinirole contained in a percentage of 0.05 to 20% by weight of the active layer, and wherein the hydrophilic polymeric substances in the active layer comprise hydroxypropylmethylcellulose and sodium carboxymethylcellulose.

25

27. A multi-layer tablet as claimed in any preceding claim, in which the active layer consists of components (i) to (iv) wherein:

- the active substance is ropinirole contained in a percentage of 0.05% to 20% by weight of the active layer,

30

- the adjuvant substances are contained in a percentage of 5% to 50% by weight of the active layer,

- the hydrophilic polymeric substances in the active layer comprise hydroxypropyl-

methycellulose and sodium carboxymethylcellulose, and

- the weight ratio of the hydrophilic polymeric substances to the lipophilic substances contained in the active layer is in the range of from 7:1 to 1:1.

5 28. A method of treating Parkinson's Disease comprising administering to a human in need of such treatment one or more multi-layer tablets as defined in any one of claims 19 to 27.

10 29. A method as claimed in claim 28, in which one or more multi-layer tablets as defined in any one of claims 19 to 27 are administered once per day to the human in need of such treatment.

30. A method as claimed in claim 28, in which a single multi-layer tablet as defined in any one of claims 19 to 27 is administered once per day.

15 31. A multi-layer tablet as claimed in any one of claims 1 to 27, in which the one or more barrier layers:

- are applied to one or both surfaces (bases) of the active layer,
- contain hydrophilic polymeric substances which swell and/or gel and/or
- 20 erode upon contact with aqueous liquids, as defined in claim 13, and
- contain lipophilic substances.

32. A multi-layer tablet as claimed in any one of claims 1 to 27 or 31, in which the one or more barrier layers:

- 25 - are applied to one or both surfaces (bases) of the active layer,
- contain hydrophilic polymeric substances which swell and/or gel and/or erode upon contact with aqueous liquids, as well as lipophilic substances,
- and
- are such that during the first hour after oral administration or
- 30 immersion in aqueous liquids (e.g. water), release of the active substance occurs substantially only from the surface of the tablet not covered by the one or more barrier layers.

33. A multi-layer tablet as claimed in any one of claims 1 to 27 or 31 to 32 wherein a barrier layer is applied to both surfaces (bases) of the active layer.

1/5




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5

2/5




FIG. 6




FIG. 7




FIG. 8

3/5




FIG. 9

4/5




FIGURE 10: Dissolution profile comparison, replication batches, dosage 0.75 mg




FIGURE 11: Dissolution profile comparison, replication batches, dosage 6 mg



5/5




FIGURE 12: Dissolution profile comparison, replication batches, dosage 12 mg




FIGURE 13: Dissolution profile comparison, replication batches, all dosages

## INTERNATIONAL SEARCH REPORT

International Application No.

No. /GB 01/01726

## A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 A61K9/24 A61K31/4045 A61P25/16

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

WPI Data, PAJ, EPO-Internal, BIOSIS

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	WO 97 03670 A (SMITHKLINE BEECHAM P.L.C.) 6 February 1997 (1997-02-06)	1-15,17, 18, 22-24, 26,31-33
A	page 7; example 8	16, 19-21, 25,27
Y	US 5 126 145 A (EVENSTAD ET AL.) 30 June 1992 (1992-06-30)	1-15,17, 18, 22-24, 26,31-33
	the whole document	
	----- -/--	

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

## \* Special categories of cited documents:

\*A\* document defining the general state of the art which is not considered to be of particular relevance

\*E\* earlier document but published on or after the international filing date

\*L\* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

\*O\* document referring to an oral disclosure, use, exhibition or other means

\*P\* document published prior to the international filing date but later than the priority date claimed

\*T\* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

\*X\* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

\*Y\* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

\*&amp;\* document member of the same patent family

Date of the actual completion of the international search

20 July 2001

Date of mailing of the international search report

30/07/2001

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Benz, K

## INTERNATIONAL SEARCH REPORT

International Application No  
PCT/GB 01/01726

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	US 6 027 748 A (CONTE ET AL.) 22 February 2000 (2000-02-22) cited in the application  column 11 -column 12; example 2 ----	1-15,17, 18, 22-24, 26,31-33
A	WO 98 30208 A (ABOTT LABORATORIES) 16 July 1998 (1998-07-16) the whole document ----	1-33
A	WO 97 48385 A (TEMPLE UNIVERSITY OF THE COMMONWEALTH SYSTEM OF HIGHER EDUCATION) 24 December 1997 (1997-12-24) page 2, line 15 -page 3, line 8 page 8, line 13 - line 21 figure 15 page 16, line 7 -page 17, line 12 -----	1-33

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

International Application No  
PCT/GB 01/01726

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9703670 A	06-02-1997	AU 6659196 A	18-02-1997
		BG 102259 A	30-09-1998
		BR 9609857 A	16-03-1999
		CN 1195986 A	14-10-1998
		CZ 9800183 A	17-06-1998
		EA 980140 A	29-10-1998
		EP 0839039 A	06-05-1998
		HU 9900299 A	28-09-1999
		JP 11509539 T	24-08-1999
		NO 980240 A	20-01-1998
		PL 324553 A	08-06-1998
		SK 5398 A	08-07-1998
		TR 9800077 T	21-05-1998
US 5126145 A	30-06-1992	AU 1822492 A	23-12-1993
		JP 5221854 A	31-08-1993
		US 5268181 A	07-12-1993
US 6027748 A	22-02-2000	IT MI970016 A	08-07-1998
WO 9830208 A	16-07-1998	AU 5609998 A	03-08-1998
		EP 0951279 A	27-10-1999
		US 6033685 A	07-03-2000
		ZA 9800080 A	08-07-1998
WO 9748385 A	24-12-1997	US 5945125 A	31-08-1999
		AU 3406497 A	07-01-1998
		CA 2258709 A	24-12-1997
		EP 0910349 A	28-04-1999
		JP 2001501591 T	06-02-2001